

Chemglaze 9995 co-reactant catalyst is used to increase the cure rate of Aeroglaze and Chemglaze C-, A-, Z-, and V-line coatings in low temperature and humidity conditions. Unlike most co-reactant catalysts, Chemglaze 9995 does not reduce the pot life of the coating.

Features & Benefits

- **Increases Cure Rate:** when used in conjunction with Aeroglaze or Chemglaze moisture-curing coatings, Chemglaze 9995 increases the cure rate in low temperature and humidity conditions, which allows for achievement of chemical resistance more quickly.
- **Multifunctional:** Chemglaze 9995 can be used with any Aeroglaze or Chemglaze C-, A-, Z-, or V-line moisture-curing polyurethane coating.

USES

Mixing

Mix the required Aeroglaze or Chemglaze coating prior to adding Chemglaze 9995 co-reactant catalyst. Refer to the appropriate technical data sheet for coating mixing instructions. Adhere to the pot life of the specific coating.

Slowly add Chemglaze 9995 while stirring the mixed coating. The amount of co-reactant catalyst that should be added is dependent on the specific coating and the temperature and humidity conditions.

Coating	Chemglaze 9995 Addition by Volume of Coating
A-Line Aeroglaze A276; Chmeaglaze A074, A080, A246	1-5%
C-Line Chemglaze C004	1-6%
V-Line Chemglaze V022, V047, V209	1-8%
Z-Line Aeroglaze Z302, Z306, Z307; Chemglaze Z001, Z051, Z202, Z252, Z306	0.5-3%

TECHNICAL CHARACTERISTICS

Typical Properties*

Property	Value
Appearance	Clear Liquid
Density, kg/L (lb/gal) ASTM D 1475-85	0.86 (7.2)
Flash Point (Seta), °C (°F) ASTM D 3278-82, Closed Cup	1 (34)

Solids Content by Weight, % ASTM D 2369-87 modified	10.35
Volatile Organic Content (VOC), g/L (lb/gal) ASTM D 3960-87	767 (6.4)

**Data is typical and not to be used for specification purposes.*

PRECAUTIONS FOR USE AND STORAGE

The shelf life is one year from date of shipment when stored in a dry, well-ventilated area at 0-32°C (32-90°F) in the original, unopened container. Do not store or use near heat, sparks, or open flames.

Before using this or any SOCOMORE product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Manufactured for SOCOMORE by: LORD Corporation, Saegertown, PA

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.