

### Approvals and conformities

AIR FRANCE	FITS 93044-04
AIRBUS	AIMS 09.08.003 type III Gr.2, IPS 09-08-003-01 / Maintenance application code 12ADB1 / CML 15-009X
AIRBUS CANADA	A2MS 565-006 Type II (conform for A220)
ALSTOM	DTRF 150 611
ATR	Item 05-027Q
BOEING	BMS 3-35 and 3-29 (NTO) (conform)
BOMBARDIER	BAMS 565-006 Type II (conform)
COMAC	CMS-CT-503 (conform)
DASSAULT AVIATION	DGQT 1.7.0.0103 Rev A
DGA (French Army)	fiche d'identification et d'utilisation n° 4214 / Attestation d'Aptitude Aéronautique n° 177
EADS CASA	Z11505
EMBRAER	MEP 10-063 (Code E1281491 & Code E7431096)
ROLLS-ROYCE	oMat 1082
SAFRAN AIRCRAFT ENGINES (formerly SNECMA)	DMR 75-621
SAFRAN HELICOPTER ENGINES (formerly TURBOMECA)	CCT 00706
SNCF (French Railways)	STM 801
Viking Air	VAMS 565-006 Type I,II,IV

**Corrosion inhibiting compound that displaces water and gives long lasting corrosion protection. Homogenous coating without runs suitable for use on a wide range of painted and unpainted metals.**

**Its main applications are the protection of surfaces, hollow bodies, frames, etc. in the aeronautical, railway and automotive industries.**

SOCOPAC 65H is very effective in reducing corrosion-linked maintenance costs; it gives excellent

water-displacement and long lasting anticorrosion protection. This combination of properties helps to increase the life and reliability of materials, preserve structures and maintain the appearance and quality of new materials. The following examples illustrate the special properties of SOCOPAC 65H.

- New concept 2 in 1:
  - very high water displacement performance with continuing water repellence in service
  - long lasting corrosion protection
- The dual function reduces the number of applications required; replacing separate products for water displacement and long term corrosion protection. For example SOCOPAC 25H and SOCOPAC 50S.
- It can be used on a large range of painted or unpainted metals (steels, aluminium and alloys, copper, titanium, cadmium, magnesium, etc.).
- The dry finish of the film makes handling pieces possible.
- Improved safety in use due to the high flash point.
- Easy, optimised application with comfortable conditions in the absence of mist during spraying. (Using low pressure spraying equipment).
- SOCOPAC 65H provides thorough protection for materials, spare parts or assemblies, in the worst climatic conditions making them absolutely water repellent and forming a very efficient barrier against all agents responsible for corrosion (water, oxygen, acids, alkalis and salts from industrial emissions, acid rain, tropical atmospheres, etc.).

## USES

---

In aerospace, it can be used when risks of corrosion by exposure to sea or corrosive air require an efficient and controllable protection: for landing gear, closed compartments, cabin and toilet under-floors, loading bays, pipe works, cables, container guide rails, etc...

In the railway industry, it is mainly used in hollow bodies, for the protection of rivets and bolts and for the protection of bogies.

## DIRECTIONS FOR USE

---

**SOCOPAC 65H** is available in liquid to be applied by

- Dipping.
- Brushing.,
- Spraying (classic spray gun, airless/airmix system, PREVAL sprayer).
- Low pressure spray system, which allows optimisation of application and users' comfort (no mist during spraying, fine regulation of flow, absence of runs and fat edges). *Example of low pressure application equipment: KREMLIN with M21 gun for flat surfaces, guns with fine nozzles and curved extensions at 45° and 135° for more difficult areas.*

**SOCOPAC 65H** is also available in aerosol and **AEROSOL EXTENDER 60cm** for application in cavities.

The operator must check that the deposited film is homogeneous and of the correct thickness. SOCOPAC 65H must be applied on clean and dry surfaces.

## REMOVAL

- **Types HYSO, SOCOSOLV or DIESTONE (used undiluted at ambient temperature):** apply the product by swabbing, low pressure spraying or by dipping. Let the solvent impregnate the coating and carry out a second application if necessary in restricted access areas. Recover the effluent from the lowest point by emptying or suction.
- **SOCOSOLV A3582 (used undiluted at ambient temperature):** apply the product by low pressure spraying or by dipping. Once the coating is impregnated, wash with water, preferably heated to 80° C (176° F). Recover the effluent from the lowest point by emptying or suction.
- **SOCOCLEAN PC1:** into circulation systems and application equipment for SOCOPAC 65H application.
- In all cases, consult the technical data sheets of the relevant products. Take the same measures as painting if spraying on the internal sides of a compartment.

## APPLICATION METHOD

All the equipment usually employed for cleaning under pressure can be used, provided the instructions on the product technical data sheets are respected and the situation is appropriate.

For further information, contact the following distributors: KREMLIN, GRACO, WAGNER, KARCHER...

## TECHNICAL CHARACTERISTICS

---

Appearance .....	thixotropic liquid
Specific gravity .....	(at 20°C/68°F) 0.93
Flash point .....	(ISO 13736) 38°C/100°F
Standard dry film thickness .....	15µ
Film appearance .....	dry, translucent
Film resistance to temperature .....	-55°C to 100°C (-67 to 248°F)
Covering power .....	30m <sup>2</sup> /L (for a dry film of 15µ); 17,5m <sup>2</sup> /L (for 25µ) ; 9m <sup>2</sup> / (for 50µ)
Film resistance to humid tropical air ... on steel and aluminium (chamber at 35°C/95°F and 100% humidity): 2000 hours (20µ)	
Resistance to salt spray fog ... ASTM B 117/BSS 7249 on steel (XC18S) : 15µ = 750 h ; 40µ = 1500 h / ASTM B 117/BSS 7249 on aluminium alloy (2024 T3): 15µ = 1500 h ; 25µ = 2000 h	
Drying time .....	fast to handling : 1 hour ; total drying : 3 hours
Estimated protection period ... from 36 months to several years, depending on the use conditions of the part/structure	

## PRECAUTIONS FOR USE AND STORAGE

---

SOCOPAC 65H is compatible with WADIS or SOCOPAC type products.

SOCOPAC 65H is free of chlorinated or aromatic hydrocarbons.

However, as for all hydrocarbon-based products, it is important to take the normal usage and storage precautions: use and store away from flames and heat sources - wear gloves when applying and eye protection when spraying.

Store in the original, tightly closed containers, protected from heat and flames - storage temperatures: from -10 to +50°C (+14 to +122° F). If possible bring the product to about 20° C (68° F) before application. Always shake well before use.

For more information regarding the danger of the product, please consult the product safety data sheet according to local regulation.

For professional use only.

**This technical data sheet replaces and cancels the previous one.**

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as SOCOMORE deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Pictures are not contractual. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.