TECHNICAL DATA SHEET

DGY12-55





Specifications

| | Dimensions mm - kg | | | | | | | Dimensions Inches - lbs | | | | | | Cold Cranking Amps | | |
|----------|--------------------|-------|--------|--------|---------|--------|--------|-------------------------|--------|--------|---------|--------|--------|--------------------|-------|--|
| | | | Height | Height | Height | | | | Height | Height | Height | | 20°C | 0°C | -18°C | |
| | Length | Width | Auto | Insert | Battery | Weight | Length | Width | Auto | Insert | Battery | Weight | (68°F) | (32°F) | (0°F) | |
| DGY12-55 | 229 | 138 | 231 | 214 | 213 | 17.7 | 9.02 | 5.43 | 9.09 | 8.43 | 8.39 | 37.0 | 569 | 444 | 294 | |

| | | | Reserve Capacity - Mins | | | | | Capacity - Ampere Hour* | | | | | | |
|----------|-------|----------------|-------------------------|------------|---------|------------|--------|-------------------------|-------|-------|-------|------|------|------|
| _ | Volts | Thread size mm | 75 Amps | 25 Amps | 20 Amps | 15 Amps | 8 Amps | 100 Hr | 48 Hr | 20 Hr | 10 Hr | 5 Hr | 3 Hr | 1 Hr |
| DGY12-55 | 12 | 6 | 19 | 86 | 120 | 168 | 351 | 68.7 | 64.5 | 59.7 | 54.9 | 49.7 | 45.4 | 36.7 |

Dimensions





Applications









CYCLIC STATIO


SOLAR

MARINE

TECHNICAL DATA SHEET

DGY12-55

Charging



Nominal voltage 6 & 12 volts

Design life 12 Years @ 20°C

Operating temperature -10 °C to 50°C

Grid alloy Calcium / Tin lead alloy

Plates Flat pasted

Separator Microporous Duroplastic
Active Material Very high purity lead
Case and cover ABS (VO on request)
Charge voltage Float 2.27 - 2.30 VPC @ 20°C

Cycling 2.40 @ 20°C

Max. 2.4 VPC Max ripple 3.5%

Charging V

Electrolyte Sulphuric acid analytical grade

purity

CHARGING CHARACTERISTICS

Floating - The optimum float voltage for a battery is temperature dependant, at 15 - 24° C the recommended value is 2.27 - 2.30V. It is recommended that battery installation sites are temperature controlled, however float voltage can be increased or decreased to compensate for temperature variations. Adjustment is calculated at +/- 3 mV per degree C.

| Operating Temperature | Recommended Applied Float Voltage VPC | | | | | | |
|--------------------------|---|--|--|--|--|--|--|
| 0-9 | 2.33-2.35 | | | | | | |
| 10-14 | 2.30-2.33 | | | | | | |
| 15-19 | 2.27-2.30 | | | | | | |
| 20-24 | 2.27-2.30 | | | | | | |
| 25-29 | 2.25-2.27 | | | | | | |
| 30-34 | 2.23-2.25 | | | | | | |
| 35-40 | 2.21-2.23 | | | | | | |

The most suitable charging method for battery life and performance is the constant voltage method with a limited initial current, usually limited to a maximum of $C_{20}/4$. For cyclic use we specify a short constant current phase at the end of normal charging, consult us for further details.

Charging - To obtain maximum cycle life from your battery, it is important that a suitable charging profile is used. For information about our range of chargers and our recommended charging profile, please contact us.

