

## General properties

Density	DIN 53479	g/cm <sup>3</sup>	0,96
Carbon black content	ISO 6469	%	2,4

## Mechanical properties

Tensile modulus	ISO 527	MPa	
Yield stress	ISO 527	MPa	>20
Tensile strength at break	ISO 527	MPa	
Elongation at break	ISO 527	%	> 200
Charpy notched impact strength at 23°C	ISO 179	kJ/m2	nb
Charpy unnotched impact strength at 23°C	ISO 179	kJ/m2	nb
Charpy impact strength with 15° V-notch	ISO 179	kJ/m2	
Hardness	ISO 868	Shore D	57
Wear resistance	Sand-Slurry		

## Thermal properties

Melting temperature	DIN 53736	°C	135
Thermal conductivity	DIN 52612	W/(m·K)	0,4
Coefficient of linear thermal expansion (CLTE)	DIN 53752	K <sup>-1</sup>	1,5-2×10 <sup>-4</sup>
Vicat softening temperature - A50	ISO 306/A50	°C	118
Vicat softening temperature - B50	ISO 306/B50	°C	
Service temperature (intermittent)		°C	90
Service temperature (long term)		°C	-50...80

## Electrical properties

Volume resistivity	DIN IEC 60093	Ω·cm	> 10 <sup>12</sup>
Surface resistivity	DIN IEC 60093	Ω	> 10 <sup>12</sup>
Dielectric strength	DIN 53481	kV/mm	>30
Water absorption	24h/RT	%	<0,01
OIT (200 °C)	EN 728	min	>20
Flammability (thickness 3 mm)	UL94		HB

## TECHNICAL DATA IS GIVEN AS GUIDANCE ONLY

The information data contained herein is believed to be reliable to the best of our knowledge but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom, and it is the end user responsibility to make its own determination of the product suitability for the intended applications.