

Technical data sheet

Senso Unik

DESCRIPTION					
Total Thickness	EN ISO 24346	mm	3.5		
Thickness of the wearlayer	EN ISO 24340	mm	0.4		
Weight	EN ISO 23997	g/sqm	4665		
Size	EN ISO 24342	mm	203 x 1219 8" x 48"	114 x 610 4" x 24"	610 x 610 24" x 24"
Number of planks /tiles and sqm per box	-	-	12 / 2.97 m²	36 / 2.51 m²	6 / 2.23 m²
CLASSIFICATION					
Norm/Product Specification	-	-	EN ISO 11638		
	ASTM F 1700	-	Class III Type B		
European Classification	EN ISO 10874	class	23-32		
Fire Rating	EN 13 501-1	class	Bfl-s1		
Static Electrical Propensity	EN 1815	kV	< 2		
Slip Resistance Wet	EN 16165 annex B	class	R9		
PERFORMANCES					
Wear Resistance	EN 660.2	mm3	< 2.0		
Wear Group	QB 30	group	T		
Type Binder content	EN ISO 11638	group	I		
Room Impact	NF S 31074	dB	72		
Impact sound insulation	EN ISO 717-2	dB	17		
Dimensional stability (norm)	EN ISO 23989	%	≤ 0.15		
Dimensional stability (average measured value)	-	%	≤ 0.10		
Residual Indentation	EN ISO 24343-1	mm	≤ 0.15		
Castor chair test	ISO 4918	-	OK		
Thermal Conductivity	EN ISO 10456	W/(m.K)	0.25		
Colour Fastness	EN 105 - B02	degree	≥ 6		
Surface Treatment	-	-	PUR+ MATT		
Chemical Products Resistance	EN ISO 26987		OK		
ENVIRONMENT / INDOOR AIR QUALITY					
TVOC after 28 days	ISO 16000-6	µg/ m3	< 100		
CE MARKING					
CE	EN 14041				
	20				



Gerflor®