

## **TECHNICAL DATA SHEET**



# **DECKING OIL**

#### **PRODUCT DESCRIPTION**

DECKING OIL is an impregnation oil for the protection and maintenance of all exterior wood. Decking oil has a built-in UV blocker, which slows down discolouration of the wood. Decking oil feeds and protects the wood and provides a water resistant effect. DECKING OIL is suitable for all wooden decks, outdoor furniture and sidings. Regular use of Decking oil increases the lifespan of your exterior wood.

## **TECHNICAL DATA**

SOLID CONTENT	57%
DENSITY	0,90
COLORS	CLEAR, PINE, TEAK, LIGHT OAK, DARK OAK, BANKIRAI, LIGHT GREY, DARK GRAY

#### **PRE-TREATMENT**

Before applying Decking oil, the wood should be cleaned with Woodcleaner Ciranova. Ensure that all dirt, moss and algae is removed before applying the Decking oil.

#### **USER INSTRUCTIONS**

Apply the Decking oil with a brush or pad in the direction of the boards. Let it soak in for a few minutes and remove the excess oil within 30 minutes, by polishing them with a white pad or a cloth.

If necessary, a 2nd layer can be applied after approx. 8 hours. Ensure that the wood is well-saturated for long-term protection.

When using the decking oil on furniture, the excess oil must be wiped off, until the surface feels dry to the touch.



## **DRYING TIME**

After approx. 12 hours, depending on the type of wood and the environmental conditions (temperature, humidity, etc.), the surface will be slightly walkable.



#### **APPLYING QUANTITY**

Approx. 12-15  $\,\mathrm{m}^2$ /litre per layer, depending on the type of wood.

# AFTER TREATMENT

To increase the lifespan of your exterior wood, it is recommended to apply a new layer of Decking oil once or twice a year.

## **PRODUCT INFORMATION**

Dried oil remnants are self-ignitable. Used pads and cloths can be self-ignitable and should therefore be immersed in water after use. Shelf life: 2 years in closed and original packaging.



2,5L



Ciranova® products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

## PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48 www.ciranova.be ciranova@ciranova.be