

THERMHEX PP SANDWICH PANELS


The ThermHex PP sandwich panel production is based on the patented ThermHex process. The process enables continuous in-line lamination of thermoplastic skins onto the honeycomb cores in a fully automatic production line.

By using our lightweight panel weight savings of over 80% are possible compared to a monolithic construction. In comparison to a monolithic organosheet laminate, a sandwich of the same stiffness requires fewer layers of composite, which means considerable cost and weight savings when using the ThermHex PP sandwich panel.

The panel consists of 0°/90° cross ply laminate skin layers (CP) made of continuous glass fiber reinforced polypropylene (GF/PP). The folded honeycomb core material consists of polypropylene as well. This allows an optimal bond between core and skin layers in the lamination process by thermoplastic welding.

ADVANTAGES IN AUTOMOTIVE APPLICATIONS

- HIGH WEIGHT-SPECIFIC STIFFNESS AND STRENGTH
- WEIGHT AND COST REDUCTIONS
- REDUCED RAW MATERIAL USAGE
- 100% RECYCLABLE PP
- SHORT CYCLE TIMES
- FUNCTIONALISATION BY INJECTION MOULDING



Main automotive applications of ThermHex PP sandwich panels

THERMHEX WABEN GMBH

Merseburger Str. 235
D-06130 Halle (Saale)
Germany

Tel.: +49 345 131627-0
Fax: +49 345 131627-19
Email: info@thermhix.com
Web: www.thermhix.com

ThermHex
an econcore group company




LIABILITY FOR DEFECTS

All information provided herein is based on our current knowledge and experience. Due to the high number of possible influences during processing and application, the information does not release the processor from the necessity of carrying out his own investigations and tests. Information contained herein and explanations provided by ThermHex Waben GmbH in connection with this printed matter does not represent acceptance of a guarantee. Guarantee statements require special explicit written declarations on behalf of ThermHex Waben GmbH to be effective. The constitutions stated in this datasheet determine the properties of the delivery item extensively and conclusively. Application suggestions do not establish assurance of suitability for the recommended application.



We reserve the right to adapt the product to satisfy technical progress and new developments. We would be pleased to help with any enquiries including those related to special application issues. If the application for which our products are used is subject to statutory approval, the user is responsible for the procurement of such approval. Our recommendations do not release the user from the obligation of taking of any possible impairments to third-party rights into account and of clarifying these if necessary. Furthermore we refer to our General Terms and Conditions, especially with regard to any possible liability for defects. If you are not in possession of our General Terms and Conditions we would be pleased to supply these on request.

ThermHex
an econcore group company



THERMHEX PP SANDWICH PANELS

THERMHEX POLYPROPYLENE HONEYCOMB CORES
WITH GF/PP COMPOSITE SKINS


NEW PRODUCT

ThermHex COEX
THERMOPLASTIC HONEYCOMB CORES

WWW.THERMHEX.COM

THERMHEX PP SANDWICH PANELS

THPP80-CP580 | THPP120-CP820



TECHNICAL DATA

THPP80-CP580

	6THPP80-CP580	12THPP80-CP580	15THPP80-CP580	20THPP80-CP580
Sandwich thickness (mm)	6.0	12.0	15.0	20.0
Skin layer thickness (mm)	0.35	0.35	0.35	0.35
Core thickness (mm)	5.2	11.2	14.2	19.2
Cell size (mm)	4.0	5.0	5.0	5.0
Sandwich density (kg/m ³)	280–290	180–190	165–175	145–155
Core density (kg/m ³)	80–90	80–90	80–90	80–90
Weight per unit area (g/m ²)	1700	2240	2510	2960
Bending stiffness* (CD, L/MD, W) (Nm)	90/70	420/290	600/400	1000/420
Compressive strength (Z-direction) (MPa) (ASTM C365)	1.2	1.2	1.2	1.2
Compressive modulus (Z-direction) (MPa) (ASTM C365)	25	40	40	40
Shear strength (CD, L/MD, W) (MPa) (ASTM C273)	0.5/0.3	0.5/0.3	0.5/0.3	0.5/0.3
Shear modulus (CD, L/MD, W) (MPa) (ASTM C273)	15/6	15/6	15/6	15/6

MEDIUM DENSITY PP HONEYCOMB WITH 0.35 mm CROSSPLY SKINS FROM PP/GF UD TAPES

THPP120-CP820

	6THPP120-CP820	12THPP120-CP820	15THPP120-CP820	20THPP120-CP820
Sandwich thickness (mm)	6.0	12.0	15.0	20.0
Skin layer thickness (mm)	0.5	0.5	0.5	0.5
Core thickness (mm)	5.0	11.0	14.0	19.0
Cell size (mm)	4.0	5.0	5.0	5.0
Sandwich density (kg/m ³)	400–410	260–270	235–245	210–220
Core density (kg/m ³)	120–130	120–130	120–130	120–130
Weight per unit area (g/m ²)	2450	3200	3590	4240
Bending stiffness* (CD, L/MD, W) (Nm)	140/125	590/475	900/600	1600/700
Compressive strength (Z-direction) (MPa) (ASTM C365)	2.0	2.4	2.4	2.4
Compressive modulus (Z-direction) (MPa) (ASTM C365)	60	140	140	140
Shear strength (CD, L/MD, W) (MPa) (ASTM C273)	1.2/0.5	1.2/0.5	1.2/0.5	1.2/0.5
Shear modulus (CD, L/MD, W) (MPa) (ASTM C273)	50/16	50/16	50/16	50/16

HIGH DENSITY PP HONEYCOMBS WITH 0.5 mm CROSSPLY SKINS FROM PP/GF UD TAPES

Core material

Polypropylene (PP)

-30 to +80, short term up to +140

Temperature range (°C)

0.060–0.070

Normally inflammable, higher grades of fire-resistance can be obtained in sandwich elements when using specialised surface modification.

Excellent resistance to water, most acids, bases and salt solution, limited UV resistance

2500 × 1200

* at 400 mm span length in 3P8-test

THERMOPLASTIC HONEYCOMB SANDWICH PROCESSING

