

# SILTRUST™ RTV566-XB LOW OUTGASSING ADHESIVE

## Product Description

SILTRUST RTV566-XB silicone rubber compound is a two-part product processed and tested for applications where low outgassing is required. RTV566A-XB base compound is supplied ready to use with RTV566B-XB curing agent. RTV566-XB was developed to have similar end properties as SILTRUST™ RTV566 with a more user-friendly mix ratio. Curing occurs when RTV566A-XB is mixed with RTV566B-XB at a 10:1 by mass ratio. RTV566-XB offers a wide useful temperature range of -115°C (-175°F) to 260°C (500°F) continuously and up to 315°C (600°F) for short periods of time. This is one of the widest useful temperature ranges of any silicone elastomer. RTV566-XB can meet levels of outgassing listed in ASTM E595.

## Key Features and Typical Benefits

- Simple Processing
  - 10:1 by mass mix ratio
  - Different colored A and B components to visually verify uniform mix
  - Long working time at 77F/50%RH
- Provides low outgassing characteristics in a high vacuum environment
- Room temperature cure
- Excellent adhesion capability with primer
- Retains elastomeric properties from -115°C (-175°F) up to 260°C (500°F) continuously and up to 316°C (600°F) for short periods of time

## Typical Physical Properties

Uncured Properties	RTV566A-XB	RTV566B-XB
Consistency	Semi-flowable	Paste
Color	Red	White
Viscosity, cPs	42,700	Non-flowable paste
Specific Gravity	1.49	1.18
Work Life <sup>Δ</sup> , hours	3.8	
Tack Free Time <sup>Δ</sup> , hours	4.3	
<b>Typical Cured Properties</b>	<b>Cured at 23°C and 50% Relative Humidity for 7 Days</b>	
Hardness, Shore A	55	
Tensile Strength, MPa, (psi)	4.5 (658)	
Elongation, %	88	
Lap Shear Strength ‡, MPa, (psi)	3.2 (464)	
Total Weight Loss %*	0.34	
Volatile Condensable Material %*	0.02	

Typical properties are average data and are not to be used as or to develop product specifications.

‡: acid Etched, Bare AL 2024-T3, primed with SS4155 primer

\* Tested using ASTM E595 Conditions

## **Mixing**

Select a mixing container 4 to 5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV566-XB Part A base compound and add the appropriate amount of RTV566-XB Part B curing agent. The most commonly used mix ratio is 100 parts A to 10 parts B by weight.

Using clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

## **Deaeration**

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of 25 mm (29 inches) of mercury minimum. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using RTV566-XB for potting, deaeration may be necessary after pouring to avoid capturing air in complex assemblies.

## **Surface Preparation**

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of SILTRUST RTV566-XB silicone adhesive, parts should be as clean and dry as possible prior to the application of the primer and adhesive.

## **Bonding**

If adhesion is an important application requirement, SILTRUST RTV566-XB silicone rubber compound requires a primer. To apply the primer, thoroughly clean the surface of the substrate and let dry. Then apply a uniform film of the chosen silicone primer, such as SS4110P or SS4155, and allow the primer to air-dry for one hour or more. For more details on priming and adhesion, please refer to Momentive Performance Materials product data sheet on silicone primers.

## **Curing**

SILTRUST RTV566-XB silicone rubber compound, when properly mixed, will cure sufficiently in 24 hours at 25°C (77°F) and 50% relative humidity to allow gentle handling. For best results, especially with regard to outgassing and adhesion, cure for seven days at 23-25°C (73-77°F) and 50% relative humidity.

If this RTV silicone rubber compound is to be used at temperatures over 150°C (302°F), the cured product should be properly conditioned prior to service. Following full room temperature cure, a typical conditioning program would be eight hours at 100°C (212°F) and an additional eight hours at each 28°C (80°F) interval to the desired service temperature. Longer times at each temperature will be required for larger parts or very deep sections.

## **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement, or recommendation to practice any invention covered by any patent without authority from the owner of the patent.

## **Product Safety, Handling, and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment, if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular application(s).

## Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

#### Americas

+1 800 295 2392

Toll free\*

+704 805 6946

Direct Number

#### Latin America

##### Brazil

+55 11 4534 9650

Direct Number

#### EMEAL- Europe, Middle East, Africa & India

##### Europe

+390510924300

Direct number

#### ASIA PACIFIC

##### China

800 820 0202

Toll free

+86 21 3860 4892

Direct number

\*All American countries

##### Mexico

+52 55 2169 7670

Direct Number

##### India, Middle East & Africa

+ 91 44 71212207

Direct number\*

##### Japan

+81 3 5544 3111

Direct number

\*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.

##### Korea

+82 2 6201 4600

Direct number

##### South East Asia, Australia & New Zealand

+60 3 9206 1543

Direct number\*

\*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS, AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS, INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER") ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS, OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer unless any such modification

is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service, or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design or as a recommendation for the use of such material, product, service, or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials, Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials, Inc.



260 Hudson River Road Waterford,  
NY 12188 USA  
[momentive.com](http://momentive.com)

Copyright 2023 Momentive Performance Materials, Inc. All rights reserved.