



Marble





Royal Grey



TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	33.9 Ha
Modulus of rupture Psi [ASTM C 99]	2 400 psi
Compressive strength	20 200 psi
Flexural Strength	2 300 psi
Water absorption	0.05%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)



Sinai Pearl (Beige)




TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	38.8 Ha
Modulus of rupture Psi [ASTM C 99]	1 900 psi
Compressive strength	19 800 psi
Flexural Strength	1 900 psi
Water absorption	0.89%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)





Sinai Pearl Grey




TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	38.8 Ha
Modulus of rupture Psi [ASTM C 99]	1 900 psi
Compressive strength	19 800 psi
Flexural Strength	1 900 psi
Water absorption	0.89%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)



Royal Cream



TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	34.8 Ha
Modulus of rupture Psi [ASTM C 99]	1 800 psi
Compressive strength	18 300 psi
Flexural Strength	1 300 psi
Water absorption	0.12%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)



Beige Aton



TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	26.7 Ha
Modulus of rupture Psi [ASTM C 99]	1 400 psi
Compressive strength	10 400 psi
Flexural Strength	1 000 psi
Water absorption	1.62%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)





Egy Cecilia



TEST	RESULT
Abrasion Resistance Ha [ASTM C241/C1353]	26.7 Ha
Modulus of rupture Psi [ASTM C 99]	1 400 psi
Compressive strength	10 400 psi
Flexural Strength	1 000 psi
Water absorption	1.62%

Available Finishes (Honed – Polished – Brushed – sandblasted – tumbled – acid)





Split Face

Sinai Pearl



Royal Grey



Royal Cream



Sunny



Royal Golden



Beige Aton





Natural stone is one of the most luxurious materials available for architecture and interior design





Natural stone is an inexpensive way
to enhance the value of a building.




Granite

Black Aswan



Forsati




Gandolla



Fantastic




Grey



Halayeb



New
Halayeb



Red
Aswan



Rosa
Hoday



Verdi
Green



Verdi
Yellow

