




RELIABLE IN OIL & GAS FILTRATION



EFFICIENT FOR LIQUID FILTRATION


PRODUCT PROPERTIES:

Item	Measurement Methods	Properties	Unit
Appearance	Eyesight	Light yellow	-
Softening Point	JIS K7210-1995	152	°C
Melting Point	JIS K7210-1995	223	°C

PRODUCT SPECIFICATION:

Item	Measurement Methods	Properties	Unit
Material	-	Nylon	-
Weight Range	CNS 5610 L3080	10~100	gsm
Thickness	CNS 5610 L3080	0.05~0.2	mm
Width	Tape Measure	20~160	cm
Tensile Strength (30g)	Grab Method (MD/CD)	14/12	N/5cm
Elongation at Break	Via Tensile Test	66/68	%
Tear Strength	Trapezoid Method (MD/CD)	11/14	N
Pore Size (30g)	ASTM F316-03	30~40	micron
Defect Allowance (point count)	Acceptable number of defect point per meter	Less than 3	Point

PACKAGING & DELIVERY



SHEET



ROLL



WORLDWIDE