

Surface and anti-corrosion coating

Galva-Spray



Long-lasting cathodic corrosion protection | colour shade matching hot-dip galvanization

WEICON Galva Spray serves as permanent protective layer for all metal surfaces. It protects metals against rust and corrosion and is fast-drying and strongly adherent. The spray is resistant to salt water and fresh water and temperatures up to +300°C (+572°F). After more than 450 hours in the salt spray test according to DIN EN 9227, metal parts coated with WEICON Galva Spray did not show any corrosion. The spray can be used for repairing hot galvanized parts with matching colours, as highly effective antirust primer, e.g. for car bodypainting, as coating on welded joints and drill holes, and as conductive intermediate layer in spot-welding.

Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Processing

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our safety data sheets (www.weicon.com) must be observed.

Available sizes:

11005400 Galva-Spray, 400 ml

Technische Daten

Application area	indoor and outdoor use	
Binder	Acrylate resin	
Pigment	zinc and aluminium pigments	
Pigment purity	ca. 99.5% Al / ca. 94.0% Zn	
Metal content in dry film	~51 %	
Processing temperature	+5 to +35°C, ideally +18 to +25°C	
Recommended primer	Zinc Spray	
Consumption	150 ml/m ²	
Layer thickness with 1.5 crosswise applications approx.	20-40 µm	
dust-dry	15 min.	
cured after	12 h	
Cross cutting	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Salt spray test	DIN 50021/DIN 53167	> 450 h
Cylindrical mandrel bend test	DIN EN ISO 1519	no hairline cracking
Topcoat	not required	
Density	0,9 g/cm ³	
Temperature resistance	-50°C to +300°C	
Shelf life	24 mon.	

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.