TECHNICAL DATA SHEET

Product: 7350
Colour: White
Structure: Duralace
Composition: 92% Fibre/8% Binder
Fibre Composition: 70% Viscose/ 30% PET

PRODUCT SPECIFICATIONS

Test	Orientation	Units	Targets	Range	Methods
Weight			GSM	80	TM 1150
Dry Tensile Strength	MD		N/12plies	500	TM 1005
Dry Tensile Strength	CD		N/12plies	420	TM 1009
Wet Tensile Strength	CD		N/12plies	270	TM 1010
Thickness			mm/4plies	2.92	TM 1031
Sink Time			s	< 2	TM 1015
Absorption capacity			%	830	TM 1016

OV.01 29/Apr/2026

Plant Location/Information:
Cuijk, Netherlands

These are typical values and should not be considered as specifications. These characteristics are valid for “fresh” material and may vary over time from the date of production. Magnera reserves the right to modify the present properties according to the evolution of process and technology optimization. This information is confidential to Magnera Corporation.
©Magnera. All rights reserved.