



- The flooring shall be Polyflor SD, as manufactured by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring with static dissipative properties in 2.0mm thickness.
- It shall be homogeneous and monolayer in construction.
- The static dissipative properties must be present throughout the full product thickness.



- The flooring shall conform fully with the requirements of EN 649.
- In respect of flamespread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Bfl-S1, achieving the criteria EN ISO 9239-1  $\geq 8 \text{kw/m}^2$  and the mandatory requirement of EN ISO 11925-2 pass. It shall be tested to ASTM E648 and certified as having passed with a Class 1 rating, making it suitable for use in institutional, commercial and public buildings. Tested to ASTM E662, the flooring shall be  $< 450$ .
- With regard to EN 13893 for slip resistance, the flooring shall be classified DS, making it suitable for use in areas which are predominantly dry, but with occasional spillage.
- The product must have been fully tested for abrasion resistance to the Frick Taber test EN 660: Part 2 and be in abrasion group M, as defined in EN 649.
- With regard to static dissipative properties, the flooring must conform to the requirements of IBM specifications. When tested to EN 1081 R<sub>1</sub>/R<sub>2</sub> the flooring must have a resistance of  $< 10^9$  ohms. When tested to ESD S7.1, the flooring must have a resistance of between  $1 \times 10^6$  to  $1 \times 10^9$  ohms. Tested to BS IEC 61340-4-1 2003 R<sub>G</sub>, the flooring must have a resistance between  $1 \times 10^6$  to  $1 \times 10^9$  ohms.
- In accordance with EN 649, the in-use classification must be at least 34/43 as defined in EN 685: i.e. commercial areas with very heavy use; and light industrial areas with heavy use.
- The flooring must possess a valid Agrément certificate rating the product G5ws when laid in accordance with the instructions of Polyflor, with coved skirting and welded joints.
- The flooring must be available in 2.0 metre width, to minimise the number of joints.
- In respect of light fastness, the flooring shall have been fully tested to ISO 105-B02 Method 3 as having a pass to  $\geq 6$ .



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001: 2000.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor, to ensure product performance and achievement of electrical results outlined above.
- All joints must be welded.



- Polyflor Static Dissipative products are engineered for use where static control is required. These floorcoverings are ideal for use in telecommunications installations, computer rooms and healthcare facilities such as scanner rooms, X-ray suites and operating theatres, also suitable for use in electronics manufacturing.



- At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality.
- For information regarding handling and installation, advice on specific applications, adhesives, maintenance and chemical resistance, consult Polyflor.
- Access Panel applications require specific fitting instructions, to ensure product performance and achievement of electrical results outlined. Contact Polyflor Customer Technical Support Department on 0161 767 1111 for information.

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK  
 TEL: +44 (0)161 767 1111 UK SALES DIRECT: +44 (0)161 767 1122 UK FAX: +44 (0)161 767 1128  
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM WWW.POLYFLOR.COM  
 UK SAMPLE REQUESTS: +44 (0)161 767 2551

*James Halstead*  
 FLOORING



2006

POLYFLOR  
**ESD**

POLYFLOR SD

## PRODUCT SPECIFICATION

**POLYFLOR**  
 COVERING THE WORLD