

<b>PRODUCT</b>	:	<b>NEWPORT</b>
<b>DESCRIPTION</b>	:	Textured Loop Pile
<b>YARN CONSTRUCTION</b>	:	100% Statron™ Solution Dyed Nylon (Manufactured in Australia by Fibremakers – a wholly owned subsidiary of Godfrey Hirst)
<b>TOTAL PILE WEIGHT</b>	:	950 gms/m <sup>2</sup> - 28 oz/yd <sup>2</sup> (Tolerance ±5%)
<b>PILE HEIGHT</b>	:	4.0 mm (Tolerance ± 1mm)
<b>MACHINE GAUGE</b>	:	1/16 <sup>th</sup> gauge [needlepoint]
<b>PRIMARY BACKING</b>	:	Spun Bonded Polypropylene
<b>SECONDARY BACKING</b>	:	Jute/Synthetic [optional]
<b>WIDTH</b>	:	3.66 mts [broadloom]
<b>AREA OF USE</b>	:	Contract Extra Heavy Duty & Stairs Reg. No. 24214
<b>LATEX</b>	:	Synthetic
<b>ELECTROSTATIC PROPENSITY</b>	:	Permanent Conductive Fibre < 3.0 KV at 21°C and 20% RH.
<b>RADIANT HEAT SOURCE AS ISO 9239.1.2003</b>	:	CHF 6.9 kW/m <sup>2</sup> [direct stick] Smoke Value 64%
<b>STAIN PROTECTION IWS 282-1992 New</b>	:	StainWarden™ 4
<b>After 5 steam cleans</b>	:	4
<b>EXTRACTABLE MATTER Dichloromethane Extract A.S. 2001.3.4</b>	:	1.0% Maximum
<b>RESISTANCE TO INSECT PESTS A.S. 2001.6.1</b>	:	Pass
<b>TUFT WITHDRAWAL FORCE A.S. 2111.15</b>	:	30 Newtons (min)
<b>SECONDARY BACKING ADHESION A.S. 2111.16</b>	:	30 Newtons (min)
<b>COLOUR FASTNESS TO LIGHT B.S. 1006.B02</b>	:	6 (min)
<b>COLOUR FASTNESS TO SOLVENTS A.S. 2001.4.16</b>	:	4-5
<b>COLOUR FASTNESS TO SHAMPOO A.S. 2111.19.2</b>	:	4-5
<b>COLOUR FASTNESS TO RUBBING A.S. 2111.19.1</b>	:	4-5
<b>COLOUR FASTNESS TO BLEACHING A.S. 2001.4.11</b>	:	4-5
<b>COLOUR FASTNESS TO WATER A.S. 2001.4.8</b>	:	4-5
<b>VOC EMISSIONS</b>	:	Exceeds the requirement of Green Label Plus