

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** National Flooring Distributors  
13 Dulwich Street  
Loganholme QLD 4129

**Test Number :** 18-006051  
**Issue Date :** 5/02/2019  
**Print Date :** 5/02/2019

**Sample Description** Clients Ref : "Discretion"  
Cut pile tufted carpet  
Nominal Composition : 100% Nylon  
Nominal Mass per Unit Area/Density : 65oz/yd<sup>2</sup>  
Nominal Thickness : 8mm

AS/ISO 9239.1-2003

### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 10/10/2018

Date Tested 01/02/2019

CHF Value	1	2	3	Mean
Length	11.1	-	-	- kW/m <sup>2</sup>
Width	9.5	10.8	10.1	10.1 kW/m <sup>2</sup>

Smoke Value	1	2	3	Mean
Length	14	-	-	- %.min
Width	13	13	13	13 %.min

Observations:

Melting Yes

155558

31446

Page 1 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing  
- Mechanical Testing  
985

: Accreditation No.  
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.  
AWTA  
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** National Flooring Distributors  
13 Dulwich Street  
Loganholme QLD 4129

**Test Number :** 18-006051  
**Issue Date :** 5/02/2019  
**Print Date :** 5/02/2019

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23 \pm 2^{\circ}\text{C}$  and relative humidity of  $50 \pm 5\%$  for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

155558

31446

Page 2 of 2

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing  
- Mechanical Testing  
985

: Accreditation No.  
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.  
AWTA  
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall

0204/11/06

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR