

Natural concrete finishes fit for a modern aesthetic

Stucco Cement Finish

Concrete plastering cement finish allowing for various creative styles.

RECOMMENDED USES
For architectural, decorative, and textured concrete wall finishing

FEATURES
- Tough and durable
- Fills cracks and minor imperfections

SPECIFICATION

PAINT TYPE
100% Acrylic

PAINT FINISH
Cement Finish-Flat
Clear-Matte Gloss

COLOR
Cement Finish
Clear

PACK SIZE
Cement Finish -
20 Liter (22 Kg) set/
Clear - 1 Liter

SHELF LIFE
1 Year when stored in dry and cool conditions

APPLICATION TOOLS
Stainless Steel Trowel

DRYING TIME

Drying Time	: 2-3 days
Recoating Interval	: 6-8 hours

PRACTICAL COVERAGE
Cement Finish - 15sqm/set/2 coats

CLEAN-UP
Clean Water

PRODUCT PREPARATION
- Mix Part A of Wall Art Industria to Part B using an electric drill mixer. Adjust ratio as needed to achieve desired consistency.
- Blend until the mixture is lump free and homogenous. Use a big container for bigger volumes of mixtures. Do not add water while mixing, or after desired consistency is achieved.

STORAGE AND HANDLING
- Keep the container closed when not in use.
- Store in a cool, dry and well-ventilated space.
- Do not transfer contents to other containers for storage.
- In case of spillage absorb with inert materials such as sand.

DAVIES Paint Reinvented

SURFACE PREPARATION

Concrete Surfaces

A. New Painting

- All surfaces must be clean, dry, free from dust, dirt, chalk, laitance, efflorescence, rust, grease, oil, and all other foreign materials.
- Allow new concrete to cure and dry completely for at least 28 days with a moisture content of less than 15% and a Ph level below 10.
- To neutralize and remove efflorescence, treat surfaces with **DAVIES® 100-X Concrete Neutralizer** diluted with 16 parts water to 1 part DV 100-X. Apply by brush or mop to wet surface thoroughly and dry overnight. Rinse with water and dry.
- When applying Rendering Paste or Skimcoat for rough surfaces, concrete may be cured for only 7-14 days. Use **MONDO™ SK-1 Skimcoat Superfine White Powder** or **MONDO™ SK-2 Rendering Paste.**

B. Repainting

- Remove mold and mildew growth with **DAVIES® 500-X Mildewcide Wash Solution**. Rinse with water, dry and immediately apply the recommended paint system to prevent regrowth of mold and mildew.
- For surfaces that exhibit severe chalk, apply one coat of **DAVIES® 5-530 Liquid Tile™ Penetrating Sealer** or **DAVIES® 555 Concrete Clear Sealer.**
- Repair uneven surfaces with **DAVIES® 5000 Concrete Putty** or **DAVIES® 5-900 Liquid Tile™ Cast.**



CEMENT FINISH



COLORED CEMENT

APPLICATION



STEP 1

Lightly mist concrete surface with water, or dampen with a wet cloth before application.



STEP 2

Apply Wall Art Industria mixture thinly on the surface with a stainless steel trowel. For the first coat, apply evenly at around 1mm thick. Allow six (6) - eight (8) hours drying before applying the second coat.



STEP 3

Once fully dry, lightly sand uneven areas of the surface.



STEP 4

Apply second coat of Wall Art™ Industria™ mixture to level and create desired design effect. Polish the surface using a stainless steel trowel.



STEP 5

Allow the surface to dry for 2-3 days before sanding rough edges. Apply Wall Art™ Industria™ Clear Topcoat for maximum protection.