

PEEK

Chemical Designation PEEK (Polyetheretherketone) **Colour** beige opaque **Density** 1.31 g/cm³

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)	1mn/min	4200	MPa	DIN EN ISO 527-2	1)
Tensile strength	50mm/min	116	MPa	DIN EN ISO 527-2	
Tensile strength at yield	50mm/min	116	MPa	DIN EN ISO 527-2	
Elongation at yield	50mm/min	5	%	DIN EN ISO 527-2	
Elongation at break	50mm/min	15	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	175	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mn/min, 10 N	4200	MPa	DIN EN ISO 178	
Compression strength	1% / 2% 5mn/min, 10 N	23 / 43	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	3400	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	5)
Notched impact strength (Charpy)	max. 7,5J	4	kJ/m ²	DIN EN ISO 179-1eA	
Ball indentation hardness		253	MPa	ISO 2039-1	6)
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		150	°C	DIN EN ISO 11357	1)
Melting temperature		342	°C	DIN EN ISO 11357	
Service temperature	short term	300	°C		2)
Service temperature	long term	260	°C		
Thermal expansion (CLTE)	23-60°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	100-150°C, long.	7	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specific heat		1.1	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.27	W/(K*m)	ISO 22007-4:2008	
Electrical properties	parameter	value	unit	norm	comment
Specific surface resistance		10 ¹⁴	Ω	DIN IEC 60093	
Specific volume resistance		10 ¹⁴	Ω*cm	DIN IEC 60093	
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	1)
Resistance to hot water/ bases		+	-		2)
Resistance to weathering		-	-		3)
Flammability (UL94)	listed (value at 1.5mm)	V0		DIN IEC 60695-11-10;	

- (1) For tensile test: specimen type 1b
- (2) For flexural test: support span 64mm, norm specimen.
- (3) Specimen 10x10x10mm
- (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
- (5) For Charpy test: support span 64mm, norm specimen.
n.b. = not broken
- (6) Specimen in 4mm thickness

- (1) Found in public sources.
- (2) Found in public sources. Individual testing regarding application conditions is mandatory.

- (1) Ø ca. 50mm, h=13mm
- (2) + good resistance
- (3) - poor resistance