

## **FEATURES**

- Good thermal conductivity
- Compliancy high compressibility 90%
- Low hardness
  (Shore 00)
- Low oil bleed long term stability
- Electrical insulating

# Thermal Interface Sheet, 4W/m-K, 150 x 150mm 2mm, Self-Adhesive

RS Stock No.: 707-4761



RS Professionally Approved Products bring to you professional quality parts across all product categories. Our product range has been tested by engineers and provides a comparable quality to the leading brands without paying a premium price.



#### **Product Description**

RS PRO range of mid performance thermally conductive gap filler which due to their flexible design allows them to fill the air gap between uneven surfaces. Thermal gap pads provide a thermal interface between heatsinks (devices or substances for absorbing unwanted or excess heat) and electronic devices. They're particularly useful where air gaps, rough surface textures or uneven surface topography prevent the use of traditional grease or paste

Options include the following with various thicknesses and thermal conductivity:

707-4730 - 0.5 mm, 2W/mK 707-4749 - 1.0 mm, 2W/mK 707-4742 - 1.5 mm, 2W/mK 707-4746 - 2.0 mm, 2W/mK 707-4755 - 0.5 mm, 4W/mK 707-4758 - 1.0 mm, 4W/mK 707-4752 - 1.5 mm, 4W/mK 707-4761 - 2.0 mm, 4W/mK 707-4768 - 1.0 mm, 6W/mK 707-4777 - 1.5 mm, 6W/mK 707-4770 - 2.0 mm, 6W/mK

<u>707-4774</u> - 0.5 mm, 12W/mK <u>707-4783</u> - 1.0 mm, 12W/mK

#### **General Specifications**

Material	Gel					
Self-Adhesive	Yes					
Colour	Blue					
Applications	Flat panel displays; LED (light emitting diode) displays; Engine control units; Computer hard drives; Wireless communication hardware					
Flame Rating	V0 UL94					
Shelf Life	24months					



### **Electrical Specifications**

Dielectric Strength	6kV/mm
Dielectric Constant at 1kHz	5
Volume Resistivity	10 <sup>12</sup> ohm.cm
Insulation Strength	15kV/mm

#### Mechanical Specifications

Dimensions	150x150mm
Thickness	2mm
Length	150mm
Width	150mm
Diameter	75mm
Thermal Conductivity	4W/(m.K)
Hardness	Shore OO 40
Thermal Impedance	<0.28°C-in²/W
Specific Gravity	2.8g/cm <sup>3</sup>
Weight Loss	<1%
Elongation	100%
Tensile Strength	19Kgf/cm <sup>2</sup>
Density	3.3g/cm <sup>3</sup>
Deflection At 10 psi	3%
Young's Modulus	24N/cm <sup>2</sup>
Compression Ratio at 1mm, 40psi	40%
Thermal Resistance	0.8W/m.K
Coefficient Of Thermal Expansion	250ppm/K
Dissipation Factor At 1000kHz	0.013

### **Operation Environment Specifications**

Minimum Operating Temperature	-45°C
Maximum Operating Temperature	200°C

# **Thermal Pads**



### Approvals

**Compliance/Certifications** 

CE / UR / cUR



				duct							4.5	= 0		20
	u.a	1.2	1.4	1.0	1.1	1.0	2.2	3.2	3,9	4.0	9.0	2.0	13	20
n	here	nal	Con	duct	-fivit	v 4 v	w/m	k						
9	110	16.25	: 40	(Sh	ore	00)								



# **Thermal Pads**



