



ARDEX BR 200

General Purpose Repair Mortar

Easy to use

Reinstatement of spalled concrete

Non-slump, can be trowelled or spray applied

For internal and external applications

ARDEX SINGAPORE PTE LTD
26 Tuas Ave 4 Singapore 639376
Telephone: +65 6861 7700
Fax: +65 6862 3381
Email: sales@ardex.com.sg
Website: www.ardex.com.sg

ARDEX BR 200

General Purpose Repair Mortar

DESCRIPTION

ARDEX BR 200 is a single component ready to use polymer modified cementitious repair mortar for structural repair of concrete structures. It is a medium weight repair mortar and can be applied in both vertical and overhead applications with minimum difficulty.

The high polymer content ensures low oxygen and carbon dioxide diffusion, high resistance to water penetration, chloride and sulphate attack and outstanding adhesion.

USE

- Re-instatement of concrete affected by chloride attack or carbonation
- Re-profiling of concrete surfaces precast units, curbstones etc.
- Filling of honeycombs, blow holes, tie bar holes
- Repair of spalled, cracked (static cracks only) chipped concrete surfaces
- Re-aligning walls prior to tiling

FEATURES & BENEFITS

- Pre-weight factory controlled product
- Shrinkage compensated
- High bond strength
- Suitable for both exterior and interior applications
- Non-slump and high build up to 40 mm can be achieved, depending on the geometry of the penetration

SUBSTRATE PREPARATION

The substrate must be dry, clean and sound, free of dust, loose particles, grease or any other contaminants.

Conventional curing compounds should be removed prior to the application of ARDEX BR 200. All shrinkage and non-moving structural cracks should be rooted out.

APPLICATION

New Construction:

Where ARDEX BR 200 is being applied for the

re-profiling of concrete surfaces, filling of blow holes, honeycombs, etc. ensure that the surface is damp but free of standing water.

Due to its unique properties, ARDEX BR 200 can be feather edged.

Repair Work:

Saw cut the perimeter area of the repair area, ensuring all damaged concrete is removed cutting back to sound level. Ensure that corroded reinforcement is exposed, repair defective reinforcement where necessary. Remove all traces of rust by use of power tool; wire brushing, etc.

PRIMING

All exposed reinforcement bars must be cleaned and treated with ARDEX anti-corrosion primer; ARDEX BRP 100/ARDEX BR 10 ZP SE saturate the area to be repaired, remove any access and prime the repair area with ARDEX E 670 bonding agent before installing ARDEX BR 200 repair mortar.

Re-prime if primer has dried.

MIXING

Add 4.5 ± 0.2 litres of clean water per 25 kg bag of ARDEX BR 200. Mix slowly and continuously whilst the powder is added. Mix for 2 - 3 minutes thoroughly until a smooth mortar is obtained.

PLACING

Apply the mixed ARDEX BR 200 mortar to the wet primer. The geometry of the repair will dictate the method of application. ARDEX BR 200 can be applied at 40 mm thickness in one pass. However the normal application thickness is 10 mm to 40 mm.

CURING

ARDEX BR 200 repair mortar should be cured with good site work practice.

Protect from direct sunlight and windy conditions. Best results can be obtained by using ARDEX curing agent.

ARDEX BR 200

General Purpose Repair Mortar

COVERAGE

One bag of 25 kg yield for approx. 15.5 litres or 0.016 m³.

TECHNICAL DATA

Wet Density:	2.1 – 2.3g/ml
Colour:	grey
Mechanical properties:	
Compressive Strength:	≥ 45 N/mm ²
Flexural Strength:	≥ 6 N/mm ²
Chloride Ion Content (EN 1015-17):	< 0.05%

PACKAGING

ARDEX BR 200 is packed in paper sacks incorporating a polyethylene liner – net weight 25 kg.

STORAGE

This product must be stored in unopened packaging, clear of the ground in cool dry conditions and be protected from excessive draught. If stored correctly, as detailed above, the shelf life of this product is 12 months from the date shown on the packaging.

SAFETY PRECAUTIONS

Wear suitable gloves, goggles and other protective clothing. The use of barrier creams can provide additional skin protection. When working in confined areas ensure adequate ventilations. In case of contact with skin, rinse with plenty of clean water then wash with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean

water, and then seek medical attention without delay. If swallowed, seek medical attention straightaway, do not induce vomiting. The application area or site must be in good ventilation otherwise advisable to use a portable exhaust fan.

DISCLAIMER

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for user’s consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development.

Offices in Southeast Asia:

Malaysia:

ARDEX MANUFACTURING SDN BHD (669180-X)

No.35-1, Jalan Puteri 2/3, Bandar Puteri
47100 Puchong, Selangor, Malaysia

Tel: +603 8069 1139 Fax: +603 8052 3223

Email: sales@ardex.com.sg

Thailand:

ARDEX (THAILAND) CO., LTD

969 Moo 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540 Thailand

Tel: +66 2316 3069 Fax: +66 2316 3075

Email: sales@ardex.co.th

Vietnam:

Mobile: +84 901 351 308

Email: sales@ardex.com.sg