

SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

DESCRIPTION

Two-component, surface tolerant high solid glass flake epoxy coating

PRINCIPAL CHARACTERISTICS

- Primarily designed for use in offshore splash zone maintenance
- Designed for use in heavy-duty and corrosive environments
- Outstanding sea water resistance
- Excellent corrosion resistance
- Enhanced impact and abrasion resistance
- Continues to cure when immersed in water
- Long-term protection in a single-coat application
- Resistant to well designed cathodic protection
- Suitable for application on exterior of buried pipes
- Suitable on wet blast or ultra high pressure water (UHPWW) cleaned substrates (damp or dry)

COLOR AND GLOSS LEVEL

- Yellow, black (other colors available on request)
- Gloss

Note: Epoxy coatings will characteristically chalk and fade upon exposure to sunlight. Light colors are prone to ambering to some extent in interior or exterior exposures

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.1 lb/US gal)
Volume solids	85 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 122.0 g/kg UK PG 6/23(92) Appendix 3: max. 207.0 g/l (approx. 1.7 lb/US gal) EPA Method 24: 200.0 g/ltr (1.7 lb/USgal)
Recommended dry film thickness	150 - 1000 µm (6.0 - 40.0 mils) depending on system
Theoretical spreading rate	4.3 m ² /l for 200 µm (170 ft ² /US gal for 8.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 3.5 hours Maximum: 14 days



SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

Data for mixed product**Shelf life**

Base: at least 24 months when stored cool and dry
Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Coating performance will depend upon the surface preparation degree
- For atmospheric service, abrasive blast to ISO-Sa2½ or minimum SSPC SP-6, power tool cleaned to ISO-St3 (SSPC SP-3) or hand tool cleaned to ISO-St2 (SSPC SP-2) or ultra high pressure water jet to SSPC SP WJ-2(L) / NACE WJ-2(L)
- For immersion service: steel; blast cleaned to ISO-Sa2½ (SSPC SP-10), blasting profile 40 – 75 µm (1.6 – 3.0 mils)
- Higher profiles (>75 microns, 3.0 mils) is allowable with appropriate coating thickness
- Compatible previous coat must be dry and free from any contamination

Note: Coating performance is, in general, proportional to the degree of surface preparation.

Substrate temperature and application conditions

- Substrate temperature during application should be at least 3°C (5°F) above dew point

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 75:25 (3:1)

- Thinner should be added after mixing the components
- Do not thin more than is required by appropriate application property
- Adding too much thinner results in reduced sag resistance and slower cure

Induction time

None

Pot life

2 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

4 - 8%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 3.0 mm (approx. 0.060 - 0.110 in)

Nozzle pressure

0.2 - 0.4 MPa (approx. 2 - 4 bar; 29 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 8%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.53 - 0.69 mm (0.021 - 0.027 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53

SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
200 µm (8.0 mils)	4.3 m ² /l (170 ft ² /US gal)
500 µm (20.0 mils)	1.7 m ² /l (68 ft ² /US gal)

Overcoating interval for DFT up to 500 µm (20.0 mils)							
Overcoating with...	Interval	-5°C (23°F)	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	36 hours	14 hours	7 hours	3.5 hours	2 hours	1.5 hours
	Maximum	2 months	1.5 months	1 month	28 days	21 days	14 days
epoxy coatings	Minimum	36 hours	14 hours	7 hours	3.5 hours	2 hours	1.5 hours
	Maximum	1 month	28 days	21 days	14 days	7 days	4 days
polyurethanes	Minimum	48 hours	22 hours	14 hours	10 hours	6 hours	4 hours
	Maximum	1 month	28 days	21 days	14 days	7 days	4 days

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 500 µm (20 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
-5°C (23°F)	24 hours	48 hours	30 days
5°C (41°F)	10 hours	24 hours	18 days
10°C (50°F)	5 hours	16 hours	14 days
20°C (68°F)	3 hours	8 hours	7 days
30°C (86°F)	2 hours	5 hours	5 days
40°C (104°F)	1 hour	3 hours	3 days

Notes:

- The curing time is related to the DFT of the paint and ventilation of the drying condition. High DFT and poor ventilation will slow curing
- When total DFT is higher than 1500 µm (60.0 mils), curing times have to be 2 - 2.5 times in order to obtain sufficient mechanical strength.
- Premature exposure to water will lead to whitening of dark colours when applied between tides on jetties, piling etc. this will not affect anticorrosive properties of the coating
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	3 hours
20°C (68°F)	2 hours
30°C (86°F)	1 hour

SIGMASHIELD™ 880 GF / AMERLOCK™ 880 GF

Product Qualifications

- Qualified for NORSOK M501 Rev.6 System 7A with 2 coating system

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

