

# 1. Information about the goods and manufacturer

#### Name of Goods

Dual Wall Flame-retardant Heat Shrink Tubing

#### **Description of Goods**

Irradiated Polyolefin Heat Shrink Tubing with meltable adhesive liner

## Name of Manufacturer or Supplier of the goods

Premier Farnell 150 Armley Road Leeds LS12 2QQ

Tel.: +44 (0) 870 129 8608

## **Emergency telephone number**

+44 (0) 870 202530

# 2. Chemical Properties

Ingredient	Chemical Formula	Function	Percentage	Supplier	CAS No.
Polyolefin	(CH <sub>2</sub> CH <sub>2</sub> )n	Main Material	50%	China Sinopec	9002-88-4
Magnesium hydroxide	Mg(OH)2	Flame Retardants	30%	Jinhaohui Material Co., Ltd.	1309-42-8
APP	-	Flame Retardants	10%	Shanghai Haiyi Co., Ltd	7723-14-0
Pigment	Pigment	Colorant	5%	Huawancai Co., Ltd	83524-75-8
Ho-melt Adhesive	EVA	Sealant	5%	-	-

#### 3. Hazard Information

## **Key Hazards**

Toxicological Effects on Heath

After the tubes are ignited, the flame will self-extinguish in a short time. A little fume will give off and have slight harm on the respiratory passage of the human body.

Influence on Environment

It will cause air pollution when the tubes burn.

Physical and Chemical Hazards

Normally it is in tubular shape, and shrink at 70°C to 125°C, which perhaps is harmful.

Special Hazards

When roasted or fumigated, the smoke given off will have impact on the eyes and respiratory system, and is harmful to the human body.

#### Main symptoms

Weep, sneeze, cough, etc. These symptoms can be relieved through breathing fresh air.

## Hazards generated when burning

The tubing will burn for a short period of time after being ignited.

## 4. First-Aid Measures

## First-aid measures for exposing in different occasions:

Inhalation

During proper operation, there is no danger caused by inhalation.

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk





Skin contact

No damage to skin in normal contact. As skin is easily scratched by the tubes, the operators are suggested to put on gloves in operation.

Eye contact

No harm.

Ingestion

Not edible

## Key harmful effects

It will impact the respiratory System if you inhale smokes generated by the burning of the tubes.

#### Protective measures for the rescuers

Wear respiration protection equipment.

#### Suggestions to doctor

Those who have suffered severe damage in respiratory system should keep on inhaling fresh air to relieve the symptom.

# 5. Fire-fighting Measures

#### Suitable fire-extinguishing agent

Dry Powder Extinguisher should be used in order to put out the

## Special harms possibly incurred in fire-fighting

Small amount of smoke will give off when the tubes burn, which will impact the respiratory system of human body.

## Special fire-fighting procedures

Nο

### Special protective equipment for the fire-fighters

Normal fire-extinguishing equipment.

# 6. Emergency measures for leakage

## Attentions need to be paid by individuals

Nο

#### **Environmental notice**

No

### **Cleaning Method**

No

# 7. Operation and Storage

#### Operation

The tubes will shrink when heated by oven or heat gun.

### **Storage**

Pack the tubes with cartons properly and place them at a shady place and at normal temperature.

## 8. Contact controls and personal protection:

#### **Contact controls**

Not harmful

## Personal protective measures

No

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk





# 9. Physical and Chemical Properties

#### **Outer Jacket**

Features	Properties	Test Method	Test result
Physical Properties	Tensile strength /MPa	ASTM D2671	≥10.4
	Elongation%	ASTM D2671	≥300
	Tensile strength after aging/MPa	UL 224: 158°C × 168hr	≥7.3
	Elongation after aging%	UL 224: 158°C × 168hr	≥200
	Heat Resistance	UL 224: 250°C × 4hr	No viscidity No Cracking
	Cold blend	UL 224: -30°C × 4hr	No Cracking
Electrical Properties	Dielectric Strength(KV/mm)	IEC243	≥20
	Volume resistance / Ω-cm	IEC93	≥1×10 <sub>14</sub>
Chemical Properties	Anti Corrosion	UL 224 158°C × 168hr	PASS
	Copper stability	UL 224 158°C × 168hr	PASS
	Flammability	UL 224	VW-1
	Water Absorption %	ASTM-D570	≤0.5

## Hot-melt adhesive

Properties	Test Method	Test result
Water Absorption	ASTM D570	≤0.2
Softening Point	ASTM E28	95°C
Peel Strength (PE)	ASTM D1000	120N/25mm
Peel Strength (AL)	ASTM D1000	80N/25mm

# 10. Stability and Reactivity of the goods

## Stability

Irresolvable

#### Hazardous effects under special conditions

If exposed to fire, the products will burn in a short time and give off smoke.

# Conditions to be avoided

The products will shrink under high temperature.

#### Substance to be avoided

Fire

# Hazardous decomposition product

Smoke

# 11. Toxicological Information

**Acute Toxicity** 

No

Partial Effect

Nο

Allergic Reactions

No

www.element14.com www.farnell.com www.newark.com www.cpc.co.uk





Slow toxicity or long-term toxicity

No

# 12. Ecological Information:

#### Possible effects on environment

The products are irresolvable naturally and are not harmful to animals, plants and aquatic life.

## 13. Waste Disposal:

Trash disposal

It is suggested that he waste be collected to waste-collection station for treatment.

**Special Effects** 

No

# 14. Transport Information

Regulations on international transportation

Nο

U.N. code

No

**Regulations on Domestic transportation** 

No

Special transportation method and notice

Avoid distortion caused by extrusion and damage caused by edged tools.

## 15. Regulation Information

Applicable regulation

**UL224** 

## **Part Number Table**

Description	Part Number
Heat Shrink, Black, 4mm, 1.2m	HS400
Heat Shrink, Sleeving, 6mm, 4:1	HS401
Heat Shrink, Sleeving, 8mm, 4:1	HS402
Heat Shrink, Sleeving, 12mm, 4:1	HS403
Heat Shrink, Black, 16mm, 1.2m	HS404
Heat Shrink, 20mm, Black, 1.2m	HS405
Heat Shrink, Adhesive, Black, 24mm, 1.2m	HS406

Description	Part Number
Heat Shrink, Adhesive, Black, 32mm, 1.2m	HS407
Heat Shrink, Sleeving, 52mm, 4:1	HS408
Heat Shrink, Sleeving, 4mm, 4:1, 5m	HS409
Heat Shrink, Sleeving, 6mm, 4:1, 5m	HS410
Heat Shrink, Sleeving, 8mm, 4:1, 5m	HS411
Heat Shrink, Sleeving, 12mm, 4:1, 5m	HS412

Important Notice: This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. pro-POWER is the registered trademark of the Group. © Premier Farnell plc 2012.



