

WEICON Casting Resin MS 1000



**liquid
unfilled
low viscosity pure epoxy resin**

WEICON MS 1000 Casting Resin is suitable for the most diverse applications, such as for casting electrical components, and can be blended by various fillers (in form of powder, fibres and fabric), e.g. for the production of highly filled backfilling compounds.

WEICON MS 1000 Casting Resin can be used in the electrical industry, in machine construction and in many other applications.



Technical Data

Composition	Epoxy resin unfilled
Specific Properties	liquid
Colour after curing	transparent, slight inherent colour
Mixing ratio by weight resin/hardener	100:20
Density of the mixture (200g preparation)	1,1 g/cm ³
Viscosity of the mixture	1.300 mPa·s
Consumption at a coating thickness of 1,0 mm	1,10 kg/m ²
Maximum layer thickness for each working step	10 mm
Pot life at +20°C (+68°F) 200g preparation	20 min.
Curing time mechanical loads	24 h
Final strength after	36 h
Mean strength at +25°C (+77°F) acc. to DIN 53281-83 ASTM D 1002:	

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Pressure	60 Mpa
Bending	41 Mpa
E-Modul	2.900 Mpa
Shore D (ATSM D 1706)	80
Shrinkage	0,2 %
Thermoforming resistance	+50 °C
Temperature resistance	-35 to +120 °C
ISSA-Code	75.509.36
IMPA-Code	81 29 85

Information about surface pre-treatment and processing can be found in the manual.

Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +25°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10520010 WEICON Casting Resin MS 1000 1.0 kg

Accessories:

10519250 Colour Paste Black, 250 g
 10604025 Mould Release Agent Liquid F 1000, 250 ml
 10604515 Mould Release Agent Wax P 500, 150 g
 10850005 Glass Fibre Cloth Tape, 50 mm
 10953001 Processing Spatula, short
 10953003 Processing Spatula, long
 10953010 Stirrer Stainless Steel,
 11202400 Sealant and Adhesive Remover, 400 ml
 11207400 Surface Cleaner, 400 ml
 11450400 Mould Release Agent, 400 ml
 11850200 Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG
 (Headquarters)
 Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Turkey
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr
 www.weicon.com.tr

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON South East Asia Pte Ltd
 Singapore
 phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weiconcz.cz

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es