

Technical Datasheet

Create Date: 16.11.2017 - Seite 1/

Adhesive Spray



universal use

WEICON Adhesive Spray can be used universally and bonds light materials to themselves and among each other.

Adhesive Spray is suitable for the bonding of numerous materials such as paper, cardboard, pasteboard, wood, thin veneers, cork, leather, textiles, felt, soft foam, rubber, foam rubber, and plastic film (except for PVC and polyethylene). It is especially suited for the bonding of hard foam (e.g. polystyrene).

Technical Data

Base	synthetic rubber
Processing temperature	+10 to +30 °C
Evaporation time	5 - 15 min.
Open time max.	30 min.
Effectivness	4 m²
Temperature resistance	-20 to +65 °C
Storage stability	12 months

Processing

- 1. Shake can before use. Surfaces must be dry, clean and free of grease. Spray on one surface at about 15 to 30 cm distance. With porous materials, Adhesive Spray should be applied on both surfaces.
- 2. Depending on surface characteristics and ambient temperature, let the spray dry for 1 15 minutes until the adhesive is no longer stringy.
- 3. Position the parts and join them with strong pressure.
- 4. The spray head can be set to horizontal or vertical spray jet

Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

11800500 Adhesive Spray 500 ml

Accessories:

11202400 Sealant and Adhesive Remover, 400 ml

11207400 Surface Cleaner, 400 ml 11850200 Hand Protective Foam, 200 ml

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon es WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com