

Safety Data Sheet

LOCTITE 493

Page 1 of 9

SDS No. : 153539 V001.6 Revision: 01.07.2016 printing date: 18.12.2019

Section 1. Identification of the substance/preparation and of the company/undertaking		
Product name:	LOCTITE 493	
Other means of identification: Product code: Recommended use of the chemica	LOCTITE 493 BO50G EGFD IDH234058 Il and restrictions on use	
Intended use:	Adhesive	
Identification of manufacturer, importer or distributor Importer: Henkel Singapore Pte Ltd 401 Commonwealth Drive, #03-01/02, Haw Par Technocentre, Singapore. 149598 Phone : +65 62660100 Fax : +65 62661161		
E-mail address of person responsible for Safety Data Sheet:	ap-ua-psra.sea@henkel.com	
Emergency information:	FOR EMERGENCIES ONLY (Spill, major leak, Fire, Exposure, or Accident). Call CHEMTREC: +1 703-741-5970	

Section 2. Hazards identification

GHS Classification:

Hazard Class	Hazard Category
Skin corrosion/irritation	Category 2
Serious eye damage/eye irritation	Category 2
Specific target organ toxicity -	Category 3
single exposure	

GHS label elements:

Hazard pictogram:

Signal word:

Warning

<u>Target organ</u>

respiratory tract irritation

Hazard statement:	H315 Causes skin irritation. H319 Causes serious eye irritation. H335 May cause respiratory irritation.
Precaution:	
Prevention:	P261 Avoid breathing dust/fume/gas/mist/vapours/spray.P264 Wash hands thoroughly after handling.P280 Wear protective gloves/protective clothing/eye protection/face protection.
Response:	 P302+P352 IF ON SKIN: Wash with plenty of water. P304+P340+P312 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell. P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P333+P313 If skin irritation or rash occurs: Get medical advice/attention. P337+P313 If eye irritation persists: Get medical advice/attention. P362+P364 Take off contaminated clothing and wash it before reuse.
Storage:	P403+P233 Store in a well-ventilated place. Keep container tightly closed.
Disposal:	P501 Dispose of contents/container to an appropriate treatment and disposal facility in accordance with applicable laws and regulations, and product characteristics at time of disposal.

Section 3. Composition / information on ingredients

Substance or Mixture: Mixture

Declaration of hazardous chemical:

Hazard component CAS-No.	Content	GHS Classification
Mecrilate	60- 100 %	Skin irritation 2
137-05-3		H315
		Serious eye damage/eye irritation 2
		H319
		Target Organ Systemic Toxicant - Single exposure 3
		H335
Hydroquinone	< 0.1 %	Acute toxicity 4; Oral
123-31-9		H302
		Serious eye damage/eye irritation 1
		H318
		Skin Sensitization 1
		H317
		Germ cell mutagenicity 2
		H341
		Carcinogenicity 2
		H351
		Acute hazards to the aquatic environment 1
		H400
		Chronic hazards to the aquatic environment 1
		H410

Inhalation:	Move to fresh air, consult doctor if complaint persists.
Skin contact:	Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such a spoon, preferably after soaking in warm soapy water. Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate enough heat to cause a burn. Burns should be treated normally after the adhesive has been removed from the skin. If lips are accidentally stuck together apply warm water to the lips and encourage maximum wetting and pressure from saliva inside the mouth. Peel or roll lips apart. Do not try to pull the lips apart with direct opposing action.
Eye contact:	If the eye is bonded closed, release eyelashes with warm water by covering with wet pa Cyanoacrylate will bond to eye protein and will cause periods of weeping which will he to debond the adhesive. Keep eye covered until debonding is complete, usually within 1-3 days. Do not force eye open. Medical advice should be sought in case solid particles of cyanoacrylate trapped behind the eyelid cause any abrasive damage.
Ingestion:	Ensure that breathing passages are not obstructed. The product will polymerise immediately in the mouth making it almost impossible to swallow. Saliva will slowly separate the solidified product from the mouth (several hours).
Indication of immediate medical attention and special treatment needed:	See section: Description of first aid measures
	Section 5. Fire fighting measures
Suitable extinguishing media:	Foam, extinguishing powder, carbon dioxide. Fine water spray
Specific hazards arising from the chemical:	In the event of a fire, carbon monoxide (CO) and carbon dioxide (CO2) can be released In case of fire, keep containers cool with water spray.
Special protection equipment and precautions for firefighters:	Fire fighters should wear positive pressure self-contained breathing apparatus (SCBA).

Section 6. Accidental release measures

Personal precautions:	Ensure adequate ventilation.
Environmental precautions:	Do not let product enter drains.
Clean-up methods:	Do not use cloths for mopping up. Flood with water to complete polymerization and scrape off the floor. Cured material can be disposed of as non-hazardous waste.

Section 7. Handling and storage		
Handling:	Ventilation (low level) is recommended when using large volumes Use of dispensing equipment is recommended to minimise the risk of skin or eye contact	
Storage:	For optimum shelf life store in original containers under refrigerated conditions at 2 - 8° C (35.6 - 46.4 °F)	

Section 8. Exposure controls / personal protection

Components with specific control parameters for workplace:

METHYL 2-CYANOACRYLATE 137-05-3	Value type	Time Weighted Average (TWA):
	ppm	0.2
	Remarks	ACGIH
HYDROQUINONE 123-31-9	Value type	Time Weighted Average (TWA):
	mg/m ³	1
	Remarks	ACGIH
HYDROQUINONE (DIHYDROXY BENZENE) 123-31-9	Value type	Time Weighted Average (TWA):
	mg/m ³	2
ĺ	Remarks	SG PEL

Respiratory protection:	Ensure adequate ventilation. An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area Filter type: A (EN 14387)
Hand protection:	Chemical-resistant protective gloves (EN 374). Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374): nitrile rubber (NBR; >= 0.4 mm thickness) Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374): nitrile rubber (NBR; >= 0.4 mm thickness) This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g. temperature). If signs of wear and tear are noticed then the gloves should be replaced. Polyethylene or polypropylene gloves are recommended when using large volumes. Do not use PVC, rubber or nylon gloves. Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed then the gloves should be replaced. The use of chemical resistant gloves such as Neoprene or Natural Rubber is recommended
Eye protection:	Wear protective glasses. Protective eye equipment should conform to EN166.
Body protection:	Wear suitable protective clothing. Protective clothing should conform to EN 14605 for liquid splashes or to EN 13982 for dusts.
Engineering controls:	Ensure good ventilation/extraction.
Hygienic measures:	Good industrial hygiene practices should be observed. Do not eat, drink or smoke while working. Wash hands before work breaks and after finishing work.

Colorless, Straw

Appearance:

Appearance.	Coloness, buaw
	Liquid
Odor:	Irritating
Odor threshold (CA):	No data available.
pH:	No data available.
Melting point / freezing point:	No data available.
Specific gravity:	1.1
Boiling point:	> 149 °C (> 300.2 °F)
Flash point:	80 - 93 °C (176 - 199.4 °F)
(None)	
Evaporation rate:	No data available.
Flammability (solid, gas):	No data available.
Lower explosive limit:	No data available.
Upper explosive limit:	No data available.
Vapor pressure:	0.3 mbar
Vapor density:	No data available.
Density:	1.1 g/cm3
Solubility:	No data available.
Partition coefficient: n-	No data available.
octanol/water:	
Auto ignition:	No data available.
Decomposition temperature:	No data available.
Viscosity:	No data available.
VOC content: (2010/75/EC)	< 3.00 %

Section 10. Stability and reactivity

Reactivity/Incompatible
materials:
Chemical stability:
Conditions to avoid:
Hazardous decomposition
products:

Rapid exothermic polymerization will occur in the presence of water, amines, alkalis and alcohols.Stable under recommended storage conditions.Stable under normal conditions of storage and use.None if used for intended purpose.

Section 11. Toxicological information

Symptoms of Overexposure:

EYE: Irritation, conjunctivitis. SKIN: Redness, inflammation. RESPIRATORY: Irritation, coughing, shortness of breath, chest tightness.

Acute oral toxicity:

Mecrilate	Value type	LD50
137-05-3	Value	>4,440 mg/kg
	Species	rat
	Method	OECD Guideline 423 (Acute Oral toxicity)
Hydroquinone	Value type	LD50
Hydroquinone 123-31-9	Value type Value	LD50 367 mg/kg
· ·		

Acute dermal toxicity:

Mecrilate	Value type	LD50
137-05-3	Value	> 2,000 mg/kg
	Species	rabbit
	Method	OECD Guideline 402 (Acute Dermal Toxicity)

Skin corrosion/irritation:

Mecrilate	Result	irritating
137-05-3	Exposure time	24 h
	Species	rabbit
	Method	

Serious eye damage/irritation:

Mecrilate	Result	irritating
137-05-3	Exposure time	
	Species	rabbit
	Method	

Respiratory or skin sensitization:

Mecrilate	Result	not sensitising
137-05-3	Test type	
	Species	guinea pig
	Method	Not specified
Hydroquinone	Result	sensitising
123-31-9	Test type	Guinea pig maximisation test
	Species	guinea pig
	Method	

Germ cell mutagenicity:

Hydroquinone	Result	negative
123-31-9	Type of study / Route of administration	bacterial reverse mutation assay (e.g Ames test)
	Metabolic activation / Exposure time	with and without
	Method	EU Method B.13/14 (Mutagenicity)

Repeated dose toxicity:

Mecrilate	Result	NOAEL=> 200 mg/kg oral: feed	
137-05-3	Route of application		
	Exposure time / Frequency of treatment	90 ddaily	
	Species	rat	
	Method	OECD Guideline 408 (Repeated Dose 90-Day Oral Toxicity in Rodents)	
Hydroquinone	Result	NOAEL=>= 250 mg/kg	
123-31-9	Route of application	oral: gavage	
	Exposure time / Frequency of treatment	14 days5 days/week. 12 doses	
	Species	rat	
	Method	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)	
Hydroquinone	Result	LOAEL=<= 500 mg/kg	
123-31-9	Route of application	oral: gavage	
	Exposure time / Frequency of treatment	14 days5 days/week. 12 doses	
	Species	rat	
	Method	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)	

Section 12. Ecological information

General ecological information:

Biological and Chemical Oxygen Demands (BOD and COD) are insignificant.

Ecotoxicity:

Do not empty into drains / surface water / ground water.

Toxicity:

Hydroquinone	Value type	LC50
123-31-9	Value	0.638 mg/l
	Acute Toxicity Study	Fish
	Exposure time	96 h
	Species	Oncorhynchus mykiss
	Method	OECD Guideline 203 (Fish, Acute Toxicity Test)
Hydroquinone	Value type	EC50
123-31-9	Value	0.134 mg/l
	Acute Toxicity Study	Daphnia
	Exposure time	48 h
	Species	Daphnia magna
	Method	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Hydroquinone	Value type	EC50
123-31-9	Value	0.335 mg/l
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Hydroquinone	Value type	EC 50
123-31-9	Value	0.038 mg/l
	Acute Toxicity Study	Bacteria
	Exposure time	30 min
	Species	
	Method	

Persistence and degradability:

Mecrilate	Result	readily biodegradable
137-05-3	Route of application	aerobic
	Degradability	0 %
	Method	OECD Guideline 301 A (new version) (Ready Biodegradability: DOC Die
		Away Test)
Hydroquinone	Result	readily biodegradable
123-31-9	Route of application	aerobic
	Degradability	75 - 81 %
	Method	EU Method C.4-E (Determination of the "Ready" BiodegradabilityClosed
		Bottle Test)

Bioaccumulative potential / Mobility in soil:

Hydroquinone	LogKow	0.59
123-31-9	Temperature	
	Method	EU Method A.8 (Partition Coefficient)

Section 13. Disposal considerations

Product

Method of disposal:

Cured adhesive: Dispose of as water insoluble non-toxic solid chemical in authorised landfill or incinerate under controlled conditions. Dispose of in accordance with local and national regulations. Contribution of this product to waste is very insignificant in comparison to article in which it is used

Packaging

Disposal of uncleaned packages:	After use, tubes, cartons and bottles containing residual product should be disposed of as chemically contaminated waste in an authorised legal land fill site or incinerated. Disposal must be made according to official regulations.	
	Section 14. Transport information	
Road transport ADR: Not dangerous goods		
Railroad transport RID: Not dangerous goods		
Inland water transport ADN: Not dangerous goods		
Marine transport IMDG: Not dangerous goods		
Air transport IATA:		
Class:	9	
Packing group:	III	
Packaging instructions (passenger):	964	
Packaging instructions (cargo):	964	
UN no.:	3334	
Label:	9	
Proper shipping name:	Aviation regulated liquid, n.o.s. (Cyanoacrylate ester)	
Additional Information:	Primary packs containing less than 500ml are unregulated by this	

Section 15. Regulatory information

mode of transport and may be shipped unrestricted.

Regulatory Information: Workplace Safety And Health Act (Chapter 354A) Workplace Safety And Health (Approved Codes of Practice) Notification 2013 SS586 Specification for Hazard Communication for hazardous chemicals and dangerous good Part 1,2,3

Global inventory status:

Regulatory list	Notification
EINECS	yes
TSCA	yes
AICS	yes
DSL	yes
ENCS (JP)	yes
PICCS (PH)	yes
IECSC	yes
ISHL (JP)	yes

Section 16. Other information

Disclaimer:

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.