

Datasheet

RS PRO E-Glass Fibre Webbing

Stock No: 2035136



Technical Specifications:

Average Density	600 – 800 kg/m ³
Colour	White
Continuous Use Limit	550°C
Melting Point	840°C

Features & Benefits:

- **Perforations in tape for bolts**
- **Excellent chemical stability**
- **Resists attack from most corrosive agents**
- **Wide range of applications including**
 - **Insulation of gas and steam turbines**
 - **Insulation Linings**
 - **Wrapping of exhausts**
 - **Flange jointing**

E-Glass tape is made from texturized, continuous E-glass fibre filaments up to a maximum of 9 microns. These fibres cause considerably less irritation of the skin than coarser fibres.