



Datasheet RS PRO 25mm Wire Reinforced Glass Wick, 25m Coil

Stock No: 2035134



Technical Specifications:

Average Density	$600 - 800 \text{ kg/m}^3$
Colour	White
Continuous Use Limit	600°C
Melting Point	840°C

rspro.com

Features & Benefits:

- Excellent chemical stability
- Resists attack from most corrosive agents
- Wide range of applications including
 - Insulation of gas and steam turbines
 - Insulation Linings
 - Wrapping of exhausts
 - Flange jointing

Yarn Make Up:

•	Yarn 1	Tinned Copper Wire
•	Yarn 2	68/1/3 Continuous Filament Glass
•	Yarn 3	990 Tex 9 Micron Glass
•	Yarn 4	1430 Tex Textured Glass



