

# WEICON F2 Epoxy Resin



## viscous aluminium-filled

WEICON F2 is suited for the casting of models, moulds and templates, for the repair of porous and damaged castings, for the production of prototypes and holding devices, and for pouring out swages to test precision.

WEICON F2 can be used in tool construction, model and mould making, and in many other industrial applications.



## Technical Data

Composition	Epoxy resin aluminium-filled
Specific Properties	viscous
Colour after curing	aluminium
Mixing ratio by weight resin/hardener	100:14
Density of the mixture (200g preparation)	1,45 g/cm <sup>3</sup>
Viscosity of the mixture	200.000 mPa·s
Consumption at a coating thickness of 1,0 mm	1,45 kg/m <sup>2</sup>
Maximum layer thickness for each working step	10 mm
Pot life at +20°C (+68°F) 200g preparation	60 min.
Curing time mechanical loads	16 h
Final strength after	24 h
Mean strength at +25°C (+77°F) acc. to DIN 53281-83 ASTM D 1002:	
Pressure	43 Mpa

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Bending	26 Mpa
E-Modul	1.500 - 2.000 Mpa
Shore D (ATSM D 1706)	79
Shrinkage	0,025 %
Thermoforming resistance	+55 °C
Temperature resistance	-35 to +120 °C
ISSA-Code	75.509.11/12
IMPA-Code	81 29 33/34

Information about surface pre-treatment and processing can be found in the manual.

### Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +25°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

10200005	WEICON F2 Epoxy Resin 0.5 kg
10200020	WEICON F2 Epoxy Resin 2.0 kg

### Accessories:

10604025	Mould Release Agent Liquid F 1000, 250 ml
10604515	Mould Release Agent Wax P 500, 150 g
10850005	Glass Fibre Cloth Tape, 50 mm
10953001	Processing Spatula, short
10953003	Processing Spatula, long
10953010	Stirrer Stainless Steel,
11202400	Sealant and Adhesive Remover, 400 ml
11207400	Surface Cleaner, 400 ml
11450400	Mould Release Agent, 400 ml
11850200	Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es