

Technical Specification PVC strip curtains

Performance Test	Standard Clear Formula	Cold Formula	Unit
Shore A Hardness	75+-5	65+-5	SIIA
Brittle Point	Approx -35	Approx -45	Degrees C
Thennal conductivity	016	0.16	W/in. K
Vicat softening temp.	50	48	"C
Specific heat capacity	16	1.6	kJ/kg. K
Falling Ball Impact Test	"-20 NO Break	"-40 NO Break	Degrees C
Flexibility	"-20 NO Break	"-40 NO Break	Degrees C
Water Absoiption	0.20%	0.20%	%
Tensile Stiess	340	420	%
Tearing resistance	50	28	NIlinij
Reaction to Fire	Self-extinguishing	Self-extinguishing	o
Sound reduction	>35	>35	dB
Liglit Transmittance	86	86	%