

WEICON GL



Sprayable | mineral-filled | short processing time | extremely wear-resistant | temperature-resistant up to +180 °C (356 °F)

The epoxy resin system WEICON GL provides high abrasion resistance and serves as wear protection for heavily used surfaces. It is flowable, has a high initial strength, is mineral-filled, and resistant to chemicals. It is particularly suitable for lining heavily stressed pump casings, as wear protection for slide bearings, chutes, funnels and pipes and for the repair of castings, valves and fan blades. The product can be used in mechanical and plant engineering, in equipment engineering, and in many other areas of industry. WEICON GL is also well-suited for creating a system structure in combination with WEICON Ceramic BL. Due to the different colours of the two wear protection systems, the degree of wear can be easily determined by visual inspection.

Characteristics

Base	Epoxy
Filler	mineral
Texture	flowable
Colour	green

Processing

Processing temperature	+15°C to +40°C	
Component temperature	>3 °C above dew point	
Relative air humidity	< 85 %	
Mixing ratio by weight	100:20	
Mixing ratio by volume	100:26	
Viscosity of the mixture	at +25 °C	13.000 mPa·s
Density of the mixture	1,3 g/cm ³	
Consumption	Layer thickness 1.0 mm	1.3 kg/m ²
Max. layer thickness	per step	10 mm

Curing

Pot life	at 20 °C, 500 g batch	30 min.
Additional layer after	(35 % strength)	3,5 h
Working strength after	(80 % strength)	6 h
Final strength	(100 % strength)	8 h
Shrinkage		0,19 %

Mechanical properties after curing

- Measured after curing at		24 h RT + 4 h 60 °C
Tensile strength	DIN EN ISO 527-2	59 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	1,7 %
E-modulus (tensile)	DIN EN ISO 527-2	3300-3700 MPa
Compressive strength	DIN EN ISO 604	99 MPa
Bending strength	DIN EN ISO 178	122 MPa
Hardness (Shore D)	DIN ISO 7619	81±3
Adhesive strength	DIN EN ISO 4624	19 MPa
Taber Test	DIN ISO 9352 (H18, 1 kg, 1000 rotations)	0,7 g / 0,6 cm ³
Lap shear strength material thickn. 1,5mm DIN EN 1465		
	Steel 1.0338 sandblasted	12 MPa
	Stainless steel V2A sandblasted	10 MPa
	Aluminium sandblasted	7 N/mm ²
	Galvanized steel	4 MPa

Thermal parameters

Temperature resistance	-35°C to +180°C	
Tg after curing at room temperature	(DSC)	~ +57 °C
Tg after tempering (at 130°C)	+126	
Heat deflection resistance	DIN EN ISO 75-2	+125 °C
Thermal conductivity	DIN EN ISO 22007-4	0.23 W/m·K
Heat capacity	DIN EN ISO 22007-4	1.09 J/(g·K)

Electrical parameters

Resistance	DIN EN 62631-3-1	2,27·10 ¹⁴
Magnetic	no	

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our safety data sheets (www.weicon.com) must be observed.



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICON GL

Surface pre-treatment

The successful application of WEICON GL depends on the thorough preparation of the surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on the adhesion. Therefore, before processing WEICON GL, the following points must be observed: The surfaces must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S.

Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 ½ - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON GL, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6).

The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m². Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture.

After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied.

Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500.

After the surface pre-treatment, WEICON GL should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

Mixing

First, stir the resin. Then mix the resin and hardener together thoroughly and bubble-free for at least four minutes at 20°C (68°F). The included processing spatula or a mechanical mixer, such as the Stirrer Stainless Steel, can be used for this purpose. With mechanical mixers, a low speed of max. 500 rpm should be used. The components should be stirred until a homogeneous mixture is achieved. The mixing ratio of

the two components must be strictly observed, as otherwise, strongly deviating physical values will result (max. deviation +/- 2 %). Only prepare a batch as large as can be processed within the pot life of 30 minutes. The specified pot life refers to a material batch of 500 g and 20°C (68°F) material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins.



Application

For processing, we recommend an ambient temperature of 20°C (68°F) at less than 85% relative humidity. The highest adhesive strength is achieved when the parts to be processed are heated to >35°C (>95°F) before application. For a thin pre-coat, work WEICON GL intensively into the surface in crosswise layers using a paint brush to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, a second application with a paint brush or foam roller can be carried out straight away, until the desired layer thickness is reached. Make sure that the epoxy resin is applied evenly and without air bubbles. For a system build-up, WEICON Ceramic BL can be applied after 3.5 hours (layer sequence time). The two wear protection systems differ in colour and thus help to visually determine the degree of wear.

Curing

Final hardness is reached after 24 hours at 20°C (68°F) at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time. The following rule of thumb applies: Each increase by +10°C (50°F) above room temperature (20°C/68°F) will decrease the curing time by half. Temperatures below 16°C (61°F) increase the curing time, until at approx. 5°C (41°F) and below, almost no reaction will take place at all.

Storage

Store WEICON GL at room temperature in a dry place. Unopened containers can be stored at temperatures of +18°C to +28°C for at least 24 months after delivery date. Opened containers must be used up within 6 months.

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICON GL

Scope of delivery

Processing Spatula | Instructions for use | Gloves | Resin & Hardener

Accessories

- 10604500 Mould Release Agent Wax P 500, 0,5 kg
- 11202500 Cleaner Spray S, 500 ml, transparent
- 15200005 Cleaner S, 5 L, colourless, transparent
- 11207400 Surface Cleaner, 400 ml, transparent
- 15207005 Surface Cleaner, 5 L, transparent
- 10604025 Mould Release Agent Liquid F 1000, 250 ml, white, milky
- 10539115 Repair Stick Multi-Purpose, 115 g, vintage white
- 10400005 WEICON Ceramic BL, 0,5 kg, blue
- 10400020 WEICON Ceramic BL, 2 kg, blue
- 10850005 Glass Fibre Cloth Tape, 1 PCE, white
- 10953001 Processing Spatula, 1 PCE
- 10953003 Processing Spatula, 1 PCE
- 10953021 Flat brush, natural bristles, 1 PCE
- 10953010 Stirrer Stainless Steel, 1 PCE
- 15841500 Pump Dispenser WPS 1500, 1 PCE
- 13250001 Cartridge Gun, 1 PCE
- 52000035 Cable Scissors No. 35, 1 PCE
- 10851010 Processing Kit, 1 PCE

Recommended equipment

Angle grinder Blast machine Heating pack, hot air blower or fan heater Smoothing trowel, spatula PE foil 0.2 mm Fabric tape Paint brush, foam roller Lint-free cloths

Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
$\text{mm}/25.4 = \text{inch}$	$\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25.4 = \text{mil}$	$\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0.225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

Available sizes

- 10700005 WEICON GL, 0,5 kg, green
- 10700010 WEICON GL, 1 kg, green

	WEICON A	WEICON B	WEICON BR	WEICON C	WEICON F	WEICON F2	WEICON HB 300	WEICON SF	WEICON ST	WEICON TI	WEICON UW	WEICON WR	WEICON HP	WEICON Ceramic BL	WEICON GL	WEICON GL-S	WEICON Ceramic W	WEICON Ceramic HC 220	WEICON WP	WEICON WR2	WEICON CBC	
Repair and moulding	x	x	x	x	x	x	x	x	x	x	x	x										
Adhesive				x	x		x		x				x									
Wear protection														x	x	x	x	x	x			
Potting and gap filling	x					x						x								x	x	

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICON GL

Chemical resistance of WEICON Plastic Metals after curing* (Excerpt)

Exhaust fumes	+	Potassium carbonate	+
Acetone	o	Potassium hydroxide 0-20 % (caustic potash)	+
Ethyl ether	+	Milk of lime	+
Ethyl alcohol	o	Carbolic acid	-
Ethylbenzene	-	Creosote oil	-
Alkalis (alkaline substances)	+	Cresylic acid	-
Hydrocarbons, aliphatic (petroleum derivatives)	+	Magnesium hydroxide	+
Formic acid >10 % (methanoic acid)	-	Maleic acid (cis-ethylenedicarboxylic acid)	+
Ammonia anhydrous 25%	+	Methanol (methyl alcohol) <85 %	-
Amyl acetate	+	Mineral oil	+
Amyl alcohol	+	Naphthalene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Naphthene	-
Barium hydroxide	+	Sodium carbonate (soda)	+
Petrol (92-100 octane)	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Hydrobromic acid <10 %	+	Sodium chloride (table salt)	+
Butyl acetate	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl alcohol	+	Caustic soda	+
Calcium hydroxide (slaked lime)	+	Heating oil, diesel	+
Chloroacetic acid	-	Oxalic acid <25 % (ethanedioic acid)	+
Chloroform (trichlormethane)	o	Perchloraethylene	o
Chlorosulphuric acid (wet and dry)	-	Kerosene	+
Chlorinated water (swimming pool concentration)	+	Oils, vegetable and animal	+
Hydrochloric acid	+	Phosphoric acid <5%	+
Chromium bath	+	Phthalic acid, phthalic anhydride	+
Chromic acid	+	Crude oil	+
Diesel fuels	+	Nitric acid <5%	o
Mineral oil and mineral oil products	+	Hydrochloric acid <10 %	+
Acetic acid diluted <5%	+	Sulphur dioxide (wet and dry)	+
Ethanol <85 % (ethyl alcohol)	+	Carbon disulphide	+
Greases, oils and waxes	+	Sulphuric acid <5%	o
Hydrofluoric acid diluted	o	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Impregnating oils	+	Trichloraethylene	o
Potash	+	Xylene	-

+ = resistant 0 = for a limited time - = not resistant *The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr