

# WEICON HB 300 Epoxy Resin



**pasty**  
**steel-filled**  
**high temperature resistant**

WEICON Plastic Metal type HB 300 is pasty, steel-filled and high temperature resistant up to +200°C (briefly up to +280°C). It is processed with a mixing ratio of 1:1.

WEICON HB 300 is also suitable for applications on vertical surfaces and can be used for the repair and bonding of cast and metal parts, for filling in blow holes, for repairing damage to containers, carriages and machine parts and for sealing pumps and pipes.

WEICON HB 300 can be used in machine and system construction, in apparatus engineering, and in many other industrial applications.



## Technical Data

Composition	Epoxy resin steel-filled
Specific Properties	putty, high-temp. resistant
Colour after curing	dark-grey
Mixing ratio by weight resin/hardener	100:100
Density of the mixture (200g preparation)	2,34 g/cm <sup>3</sup>
Viscosity of the mixture	1.700.000 mPa·s
Consumption at a coating thickness of 1,0 mm	2,34 kg/m <sup>2</sup>
Maximum layer thickness for each working step	20 mm
Pot life at +20°C (+68°F) 200g preparation	30 min.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Curing time mechanical loads	12 h
Final strength after	24 h
Mean strength at +25°C (+77°F) acc. to DIN 53281-83 ASTM D 1002:	
Pressure	100 Mpa
Bending	42 Mpa
E-Modul	9.500 - 10.000 Mpa
Shore D (ATSM D 1706)	85
Shrinkage	0,015 %
Thermoforming resistance	+120 °C
Temperature resistance	-35 to +200 briefly to +280 °C
ISSA-Code	75.509.21
IMPA-Code	81 29 51

Information about surface pre-treatment and processing can be found in the manual.

### Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +25°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

10450010 WEICON HB 300 Epoxy Resin 1.0 kg

### Accessories:

10604025 Mould Release Agent Liquid F 1000, 250 ml  
 10604515 Mould Release Agent Wax P 500, 150 g  
 10850005 Glass Fibre Cloth Tape, 50 mm  
 10953001 Processing Spatula, short  
 10953003 Processing Spatula, long  
 11202400 Sealant and Adhesive Remover, 400 ml  
 11207400 Surface Cleaner, 400 ml  
 11450400 Mould Release Agent, 400 ml  
 11850200 Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG  
 (Headquarters)  
 Germany  
 phone +49 (0) 251 9322 0  
 info@weicon.de

WEICON Middle East L.L.C.  
 United Arab Emirates  
 phone +971 4 880 25 05  
 info@weicon.ae

WEICON Inc.  
 Canada  
 phone +1 877 620 8889  
 info@weicon.ca  
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
 Turkey  
 phone +90 (0) 212 465 33 65  
 info@weicon.com.tr  
 www.weicon.com.tr

WEICON Romania SRL  
 Romania  
 phone +40 (0) 3 65 730 763  
 office@weicon.com

WEICON SA (Pty) Ltd  
 South Africa  
 phone +27 (0) 21 709 0088  
 info@weicon.co.za

WEICON South East Asia Pte Ltd  
 Singapore  
 phone (+65) 6710 7671  
 info@weicon.com.sg

WEICON Czech Republic s.r.o.  
 Czech Republic  
 phone +42 (0) 417 533 013  
 info@weiconcz.cz

WEICON Ibérica S.L.  
 Spain  
 phone +34 (0) 914 7997 34  
 info@weicon.es