

**Technical Datasheet** Date: 16.11.2017 -

# **Urethane 60**



Temperature resistance	-60 to +90 °C
ISSA-Code	75.509.41
IMPA-Code	81 29 62

Information about surface pre-treatment and processing can be found in the manual.

\*or after 24 hours at room temperature + 4 hours 70°C

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

## Available sizes:

10516005 Urethane 60 0.5 kg

### Accessories:

Colour Paste Black, 250 g
Mould Release Agent Liquid F 1000, 250 ml
Mould Release Agent Wax P 500, 150 g
Processing Spatula, short
Sealant and Adhesive Remover, 400 ml
Surface Cleaner, 400 ml
Mould Release Agent, 400 ml
Hand Protective Foam, 200 ml
Primer M 100, 250 ml
Primer S 300, 250 ml

## Shore hardness: A 60

WEICON Urethanes are 2-component polyurethanes that cure at room temperature to tough rubber-like materials, remaining flexible at temperatures down to even -60°C.

WEICON Urethanes adhere to a variety of materials such as metals, concrete, rubber, wood, fibreglass and many others. They are also suitable as flexible coatings in connection with WEICON Plastic Metal (epoxy) systems.

Due to their low sensitivity to humidity they can also be used for coatings in thin layers and have a remarkably high tensile and tear strength.

## **Technical Data**

Base	Polyurethane
Colour after curing	light beige
Mixture (weight %) resin/hardener	100:150
Density of the mixture	1,04 g/cm <sup>3</sup>
Viscosity at +25°C (+77°F) resin/hardener	5.000/520 mPa·s
Viscosity of the mixture at 25°C (+77°F)	1.500 mPa⋅s
Pot-life at 20°C (+68°F) for 10ml material	25 min.
High mechanical load capacity / detachable after	12 -20 h
Final strength (100%) after	48* h
Tensile strength according to ISO 37	5,0 MPa
Elongation at break according to ISO 37	1.250 %
Resistance to further tearing	10 kN/m
Shore hardness A	60

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarance the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

Singapore phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon ca www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weiconcz.cz

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.ti www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd