

Polyethylen, HDPE	
Chemical Resistance	
Mineral lubricants	Permanent
Aliphatic hydrocarbons	Permanent
Aromatic hydrocarbons	Conditionally permanent
Benzine	Permanent
Weak mineralic acids	Permanent
Strong mineralic acids	Permanent
Weak organic acids	Permanent
Strong organic acids	Permanent
Oxidizing acids	conditionally permanent
Weak bases	Permanent
Strong bases	Permanent
Trichloroethylene	Conditionally permanent
Perchloroethylene	Permanent
Acetone	Permanent
Alcohols	Permanent
Hot water (hydrolyze resistance)	Permanent

The listed information about the characteristics and/or data are only guidance level. These values can be influenced in many ways, among other things by environmental effect. Characteristics or suitability for a concrete intended use could not be deducted by these information. Furthermore, the listed information is only general data.