

Product: iglidur[®] H1

19.11.2013

General Properties:

density:	1.53 g/cm ³
colour:	cream
saturation with moisture absorption at 23°C / 50% r. h.:	0.1 weight %
saturation with water:	0.3 weight %

Mechanical Properties:

flexural modulus:	2800 MPa
flexural strength:	55 MPa
max. permissible surface pressure at 20 °C:	80 MPa
Shore D hardness:	77

Thermal Properties:

highest long term service temperature ¹⁾ :	200°C
highest short term service temperature ^{1), 2)} :	240°C
highest short term ambient temperature ^{1), 2)} :	240°C
lowest service temperature:	-40°C

Electrical Properties:

specific volume resistivity:	>10 ¹² Ωcm
surface resistivity:	>10 ¹¹ Ω

¹⁾ relaxation possible

²⁾ without additional load; no movement

The information on this Product Data Sheet is based on our current knowledge of the specified product. None of the information comprises one or more guarantees on certain properties .

Erstellt: 19.11.2013/Dr.-Ing. Christoph Klingshirn/ Entwicklung
F-2-0034-A

Geändert:

Verteiler: Technisches Marketing, Entwicklung

i:\gleitlager\vertrieb\lisa.schulze\i\iglidur h1 product data sheet2013.doc

Stand: A

Seite 1 von 1