

ENGLISH

Datasheet RS Pro RS Series Axial Through Hole Fixed Resistor $6.8k\Omega \pm 5\% 1W - 500 \rightarrow +350$ ppm/°C RS Stock No: 739-7128



Product Details

RS Pro axial carbon resistor with $\pm 5\%$ tolerance, provides 6.8 k Ω resistance and is power rated at 1 W. The temperature coefficient of resistance is in the range -500 to +350 ppm/°C. Carbon film axial leaded resistor offers excellent long-term stability. It features standard solder-plated copper leads. Applications include automotive, telecommunication and medical equipment. A comprehensive range of high stability carbon film resistors are qualified and tested to the requirements of IEC 115 and IEC 115-2. The ruggedized welded cap and lead method of manufacture provides a considerable strength and resistance to damage. The coating materials and the colour bands are epoxy resin and are highly resistant to solvents, abrasion and chipping. Improvements in materials and processing have allowed the rated power to be improved. Excellent stability against changes in load conditions or moisture levels, with a low noise level and high reliability make these carbon film resistors suitable for a wide range of applications. Rated at 70°C in free air mounted horizontally.

Features and Benefits

- Available in resistances from 1 Ω to 9.1 m Ω
- Resistor body: 2.3 mm diameter, 6.3 mm length
- Long-term stability
- Solder plated copper leads



ENGLISH

Specifications:

Case Style	Ceramic
Diameter	3.2 mm
Dimensions	3.2 (dia.) x 9 mm
Lead Diameter	0.65 mm
Length	9 mm
Maximum Operating Temperature	+155°C
Maximum Temperature Coefficient	+350 ppm/°C
Minimum Operating Temperature	-55°C
Minimum Temperature Coefficient	-500 ppm/°C
Power Rating	1 W
Resistance	6.8 kΩ
Technology	Carbon Film
Temperature Coefficient	-500 to +350 ppm/°C
Termination Style	Axial
Tolerance	±5%
Lead Length	26 mm
Maximum Operating Voltage	400 V
Maximum Overload Voltage	800 V



ENGLISH

Carbon Film Leaded Resistor - RS Series



① Ceramic Rod	4	Non-flame Paint With Sol Vent-proof
② Tinned Iron Caps	5	Colour Code
③ Carbon Film	6	Lead Wire

Dimensions

Туре	L	D	Н	d	Weight (g) (1000pcs)
Carbon 0.125W	3.3+0.4/-0.2	1.8±0.3	29.3±2.0	0.452.3±0.03	92
Carbon 0.25W	6.3±0.5	2.3±0.3	28±2.0	0.55±0.03	155
Carbon 0.5W (H)	6.3±0.5	2.3±0.3	28±2.0	0.55±0.03	155
Carbon 1W (H)	9.0±0.5	3.2±0.5	26±2.0	0.65±0.03	352
Carbon 2W (H)	11.5±1.0	4.5±0.5	35±2.0	0.78±0.03	775

Unit: mm

Part Numbering





Derating Curve



■Hop-Spot Temperature



ENGLISH

Environmental Characteristics

ltem	Requirement	Test Method
Short Time Overload	±(0.75%+0.05Ω)	JIS-C-5201-1 5.5 RCWV*2.5 or Max. overload voltage for 5 seconds
Insulation Resistance	>1000MΩ	JIS-C-5201-1 5.6 Apply 100V _{DC} for 1 minute
Endurance	±(3%+0.05Ω)	JIS-C-5201-1 7.10 70±2°C, Max. working voltage for 1000 hrs with 1.5 hrs "ON" and 0.5 hrs "OFF"
Damp Heat with Load	100ΚΩ±3% 100ΚΩ±5%	JIS-C-5201-1 7.9 40±2°C, 90~95% R.H. Max. working voltage for 1000 hrs with 1.5 hrs "ON" and 0.5 hrs "OFF"
Solderability	90% min. Coverage	JIS-C-5201-1 6.5 245±5°C for 3 seconds
Dielectric Withstanding Voltage	Ву Туре	JIS-C-5201-1 5.7 Apply Max. Overload Voltage for 1 minute
Temperature Coefficient	< 100KΩ +350ppm~-500ppm 100KΩ~1MΩ -0ppm~-700ppm > 1 MΩ -0ppm~-1500ppm	Resistance value at room temperature and room Temperature+100°C
Pulse Overload	±(1%+0.05Ω)	JIS-C-5201-1 5.8 4 times RCWV for 10000 cycles with 1 second "ON" and 25 seconds "OFF"
Resistance To Solvent	No deterioration of coatings and markings	JIS-C-5201-1 6.9 Trichroethane for 1 min. with ultrasonic
Terminal Strength	Tensile: 2.5 kg	Direct Load for 10 seconds In the direction off the terminal leads

■ Rated Continuous Working Voltage(RCWV) = √P*R

■ Storage Temperature: 25±3°C; Humidity < 80%RH



Electrical Specifications

Max. Max. Dielectric Item Power Rating Operating **Resistance Range** Working Overload Withstanding at 70°C Temp. Range Voltage Voltage Voltage Туре ±5% Carbon 0.125W 150V 300V 300V 0.1Ω - 22ΜΩ 0.25W 250V 500V 500V 1Ω - 10ΜΩ Carbon 300V Carbon(H) 0.5W -55 ~ +155°C 500V 500V 0.1Ω - 22ΜΩ 1W 400V 800V 800V 1Ω - 10ΜΩ Carbon(H) 2W 500V 1000V 0.1Ω - 10ΜΩ 1000V Carbon(H)

Taping/Packing Specifications

Packing Methods (Ammo)



Packaging	Packing Methods				
Туре	Α	B1-B2	S		
Carbon 0.125W	52+1/-0	1.2	5		
Carbon 0.25W	52+1/-0	1.2	5		
Carbon 0.5W (H)	52+1/-0	1.2	5		
Carbon 1W (H)	52+1/-0	1.5	5		
Carbon 2W (H)	52+1/-0	1.5	10		

Unit: mm

Ammo Packing



			Unit. Init	1			
Packaging	Packing Methods			Ammo Packing			
Туре	А	B1-B2	S	Α	В	С	Qty
Carbon 0.125W	26+1/-0	1.0	5	80	105	264	5,000
Carbon 0.25W	26+1/-0	1.0	5	80	105	264	5,000
Carbon 0.5W (H)	26+1/-0	1.0	5	80	105	264	5,000
Carbon 1W (H)	73+1/-0	1.5	5	103	82	265	1,000
Carbon 2W (H)	73+1/-0	1.5	10	103	96	265	1,000

Unit: mm

RS, Professionally Approved Products, gives you professional quality parts across all products categories. Our range has been testified by engineers as giving comparable quality to that of the leading brands without paying a premium price.

ENGLISH



Marking & Resistance Tolerance

ENGLISH



±5% E-24 1.0 1.1 1.2 1.3 1.5 1.6 1.8 2.0 2.2 2.4 2.7 3.0 3.3 3.6 3.9 4.3 4.7 5.1 5.6 6.2 6.8 7.5 8.2 9.1

Cold	Digit	Multiplier	Tolerance	
	-	-	-	-
	-	10 ⁻²	-	-
	-	10 ⁻¹	±5.0%	J
	0	10 ⁰	-	-
	1	10 ¹	-	-
	2	10 ²	-	-
	3	10 ³	-	-
	4	10 ⁴	-	-
	5	10 ⁵	-	-
	6	10 ⁶	-	-
	7	10 ⁷	-	-
	8	10 ⁸	-	-
	9	10 ⁹	-	-