

Flex+bond®



elastic strong adhesion

WEICON Flex+bond is strong, permanently elastic, temperature resistant from -40°C to +90°C (-40°F to +194°F), weather resistant, resistant to UV rays, overpaintable (wet in wet), sandable, and resistant to ageing and salt water. It is free of silicone, isocyanate, halogens and solvents. WEICON Flex+bond has an ISEGA certificate and can be used as an adhesive in foodstuff technology.

WEICON Flex+bond can be used to bond nearly all materials to themselves and among each other such as metal, wood, plastic, glass, and ceramics.



Technical Data

Composition	1 C.-Polyoxypropylene
density	1,44 g/cm ³
Viscosity adhesive	paste
Stability/Run-off (ASTM D 222)	1 mm
Processing temperatur	+5 to +40 °C
Cure type	By humidity
Curing condition	+5 to +40°C and 30% to 95% rel. humidity
Skin-overtime*	25 min.
Cure speed (first 24h)	2 -3 mm
Volume change (DIN 52451)	-1 %
Gap filling up to max.	5 mm

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Gap width up to max.	25 mm
Shelf life (+5°C to +25°C / +41°F to +77°F)	12 months
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	42
Elongation at break (DIN 53504/ASTM D 2240) ± 5	650 %
Tensile strength of pure adhesive and sealant	3,3 N/mm ²
Average tensile shear strength (DIN 53283 / ASTM D 12)	2,1 N/mm ²
Tear strength (DIN 53515/ASTM D 1002)	20 N/mm ²
Movement capacity max.	15 %
Overpaintable (liquid paint) only „wet in wet“, within 3 hrs. at the latest after material app	
Building material category (DIN 412)	B 2
Temperature resistance	-40 to +90 °C
IMPA-Code	81 52 87

*Measured at 50% relative air humidity and +23°C

Surface pre-treatment

The surfaces must be clean and grease-free. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the Primer selection table. A mechanical surface pretreatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

Processing

Processing tube

Squeeze out by hand, close tube again immediately after use, opened tubes should be used up as quickly as possible.

Processing press pack

Remove original closure. Regulate discharge by smooth turning of the cap from min. to max. Press the lever and process the product. After having turned the cap into the “min.” position the valve closes automatically and the product flow is stopped.

Joining the parts to be bonded

To ensure optimal wetting, the parts must be joined before the first skin has been formed on the adhesive (skin-overtime).

Storage

When unopened and stored in a normal climate (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

13350085	Flex+bond® 85 ml white
13350200	Flex+bond® 200 ml white
13351085	Flex+bond® 85 ml grey
13351200	Flex+bond® 200 ml grey
13352085	Flex+bond® 85 ml black
13352200	Flex+bond® 200 ml black
13353085	Flex+bond® 85 ml transparent
13353200	Flex+bond® 200 ml transparent

Accessories:

11202400	Sealant and Adhesive Remover, 400 ml
11207400	Surface Cleaner, 400 ml
11850200	Hand Protective Foam, 200 ml
13550125	Primer M 100, 250 ml
13550225	Primer K 200, 250 ml
13550325	Primer S 300, 250 ml
13550425	Primer P 400, 250 ml
13559500	Smoothing Agent,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weiconcz.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es