

Windscreen Adhesive



Elastic 1-C adhesive and sealant for mounting glass and window panes | ISEGA-certified

WEICON Windscreen Adhesive is an elastic, pasty, strong 1-C adhesive and sealant based on MS-Polymer, which is specially

designed to mount glass and window panes. For example, the adhesive bonds windscreens, rear windows and side windows in powered industrial trucks, agricultural machines, and construction machines. It is also suitable for furniture manufacture or for installations in gardening and landscaping. Windscreen Adhesive provides high adhesive strength on many materials and cures with air humidity. The adhesive shows excellent ageing resistance and good UV stability.. It is joint-filling, odourless, and free of silicones, isocyanates, halogens, and solvents.

Technical Data

Base	1 C. polyoxypropylene	
Colour	black	
Cure type	moisture-curing	
Standfestigkeit_Ablauf	ASTM D 2202	1.0 mm
Density	1,44 g/cm ³	
Curing condition	from +5°C to +40°C and 30% to 95% rel. air humidity	
Processing temperature	+5°C to +40°C	
Curing speed	in the first 24 h	2 - 3 mm
Skin-over time	25 min.	
Gap bridging up to max.	5 mm	
Max. sealing joint width	25 mm	
Tensile strength	ISO 37 / S3A	3,3 N/mm ²
Medium lap shear strength (DIN EN 1465/ASTM D 1002)	2,1 N/mm ²	
Tear resistance	DIN 53515 / ASTM D 1002	20 kN/m
Volume change	DIN 52451	-1 %
Hardness (Shore A)	DIN ISO 7619	42±5
Temperature resistance	-40 °C to briefly +90 °C up to +130 °C	
Tg after curing at room temperature	~ -55 °C	
Specific resistance	> 10 ¹⁰ Ω·cm	
Building material class	DIN 4102	B 2
Shelf life	12 mon.	

Surface pre-treatment

Surfaces must be clean and free of grease. Many surface soiling, such as oil, grease, dust and dirt can be removed with WEICON

Surface Cleaner. For heavily soiled metal surfaces, we recommend Cleaner Spray S; for removing old colour residues or adhesive

residues, WEICON Sealant and Adhesive Remover is ideal. Most materials can be bonded to and among each other. For certain materials or special requirements, we recommend the use of a

bonding agent (primer). Mechanical surface pre-treatment e.g. by grinding or sanding can also improve the adhesion considerably.

Processing

Application methods Cartridge gun for 310 ml cartridges, compressed air gun, we recommend a version with piston rod (WEICON Compressed Air Cartridge Gun), automatic dosing systems. Joining the components In order to guarantee and ideal wetting, the bonding parts need to be joined, before the adhesive skins over (skin-over time).

Storage

When unopened and stored in normal climate (+23°C and 50 % rel. air humidity), WEICON Elastic Adhesives and Sealants have a shelf life of 12 months.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Windscreen Adhesive

Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

- 13955031 V-Joint Nozzle, 1 PCE
- 13250009 Compressed Air Cartridge Gun, 1 PCE
- 13250002 Cartridge Gun Special, 1 PCE
- 13250001 Cartridge Gun, 1 PCE

Available sizes:

- 13711200 Windscreen Adhesive, 200 ml, black
- 13711310 Windscreen Adhesive, 310 ml, black

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr