



Product datasheet

WOOD

WOOD is a modified PLA based type of filament, that smells and feels like wood. The filament is a bit brittle, but tough enough to be supplied in reels of 300 gram to 1kg. It prints easy, but we advise a slightly bigger nozzle to avoid blocking. Due to a low shrinkage factor WOOD will not deform after cooling. Poly Lactic Acid is a biodegradable plastic made from renewable natural resources and one of the most popular materials for 3D printing.

Dimensions

	Ø tolerance	s
1,75mm	± 0,05mm	≥ 95%
	± 0,10mm	

Physical properties

n	Testmethod	Typical value
Specific gravity	ASTM D1505	1,20 g/cc
	-	4.5 g/10 min
Tensile strength	ASTM D882	70 MPa (MD) 100 MPa (TD)
Elongation at break	ASTM D882	110% (TD)
Tensile modulus	ASTM D882	1900 MPa (MD) 2300 MPa (TD)

Thermal properties

n	Testmethod	Typical value
printing temp.	-	205-235 °C
		°C
melting temp.	-	
Melting point.	ASTM D3418	140-150 °C
vicat softening temp.	ISO 306	± 45 °C

Features:

- Feels and smells like WOOD
- Easy to print at low temperature
- Very low warping
- Biodegradable
- Preferably printed with > 0,4mm nozzle

Colours:

WOOD is available from stock in dark brown tropical wood colour

Additional info: Due to its low tendency to warp WOOD can also be printed without a heated bed. If you have a heated bed the recommended temperature is ± 35-60°C. **We advise a nozzle > 0,4mm**

WOOD can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly