



Weight(±10%): 590 gr. (*)

Class: S1 P SRC

Sizes: 38-47

Instep: 12

TECHNICAL SHEET ART. TREKKING

Description High shoe in suede leather, blue color, 100% polyester lining, Non-Metallic HRP Insole, SPORT-LITE Insole anatomic antistatic and antibacterial, double density polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant.

Plus Midsole compound particularly studied to get a soft PU density for a higher comfort.

Suggested sectors of usage Servicing , Mechanical Industry, Logistic / Packaging , Professional / Craftsman , **Care and Maintenance** clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source.



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
Toe Cap : Non-Metallic Thin Cap toe cap, impact resistant 200 J	5.3.2.3	Impact resistance	mm	14,0	≥14
	5.3.2.4	Compression resistance	mm	14,0	≥ 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and	6.2.1.1	Perforation resistance	Ν	1.100	≥ 1.100
treated with plasma				without holes	
Antistatic footwear: dissipation capacity of the electrostatic charge	6.2.2.2	Electric resistance			≥ 1,00 x 10 ⁵ Ω
		- Wet	Ω	1,40 x 10 ⁷	е
		- Dry	Ω	4,51 x 10 ⁷	≤ 1,00 x 10 ⁸ Ω
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	22,0	≥ 20
Upper : Suede leather, blue color, thickness 2,0 mm	5.4.6	Water vapour permeability	mg/cm ² h	4,0	≥ 0,8
		Coefficient of permeability	mg/cm ²	44,8	≥ 15
	5.4.3	Tearing Strength	N	175	≥ 120
Vamp & Quarter Lining: 100% honeycomb finished polyester, breathable,	5.5.3	Water vapour permeability	mg/cm ² h	6,8	≥ 2
abrasion resistant, grey colour		Coefficient of permeability	mg/cm ²	54,4	≥ 20
	5.5.1	Tearing Strength	N	25	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water Absorption	mg/cm ²	78	≥ 70
		Ability to release water		99%	≥ 80%
Sole: double density polyurethane , bending resistant, abrasion resistant, oil	5.8.2	Tearing Strength	kN/m	10,4	≥ 8
resistant, slip resistant	5.8.3	Abrasion resistance	mm ³	81	≤ 150
	5.8.4	Bending resistance	mm	2,5	≤ 4
	5.8.5	Hydrolysis	mm	1,0	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	0,3%	≤ 12%
	5.11	Slip resistance on ceramic floor with water and	flat	0,42	≥ 0,32
		detergent	inclined	0,40	≥ 0,28
		Slip resistance on steel floor with glycerine	flat	0,20	≥ 0,18
			inclined	0,17	≥ 0,13

Ride S1P style and its components: no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions

 $^{(*)}$ = Indicative weight that refers to $\frac{1}{2}$ pair in size 42