

# Silicone HT 300



## high temperature resistant

WEICON HT 300 adhesive and sealant is red, high-temperature resistant (+300°C/+572°F), free of solvents, strong, and has acetate cross-linking properties. It is resistant to weathering, ageing and chemicals and is extremely elastic (breaking elongation of approx. 300%).

HT 300 is particularly suitable for heat-exposed bonds and seals and adheres very well to steel, aluminium, glass, ceramics and many additional materials.

HT 300 can be used in industrial furnaces, flue gas systems, heating installations, exhaust gas routing, heating cabinets and in many additional areas.

## Technical Data

Base	1 C.-Polysiloxane (Acetate)
Density	1,18 g/cm <sup>3</sup>
Viscosity adhesive	pasty
Stability/Run-off (ASTM D 222)	1 mm
Processing temperature	+5 to +35 °C
Curing type	by humidity
Curing condition	+5 to +40°C and 30% to 95% rel. humidity
Skin-overtime*	8 min.
Curing speed ( first 24h)	2 -3 mm
Volume change (DIN 52451)	< -6% %
Gap filling up to max.	5 mm
Gap width up to max.	25 mm
Shelf life (+5°C to +25°C / +41°F to +77°F)	12 months
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	30
Elongation at break acc. to ISO 37, S3A	300 %
Tensile strength acc. to ISO 37, S3A	2,5 N/mm <sup>2</sup>

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Tension strength value at 100 % (ISO 37, S3A)	0,9 N/mm <sup>2</sup>
Movement capacity max.	15 %
Overpaintable (liquid paint)	No
Building material category (DIN 412)	B 2
Temperature resistance	-40 to +280 briefly (approx. 2 h) to +300 °C
ISSA-Code	75.634.20/21
IMPA-Code	81 52 82/83

\*Measured at 50% relative air humidity and +23°C

## Surface pre-treatment

The surfaces must be clean and free of grease. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the primer selection table. A mechanical surface pre-treatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

## Processing

Processing cartridge

Application methods: Hand cartridge gun for 310 ml cartridges, compressed air gun (we recommend a variation with piston rod), automatic dosing systems.

Processing tube

Squeeze out by hand, close tube again immediately after use, opened tubes should be used up as quickly as possible.

Joining the parts to be bonded

To ensure optimum wetting, the parts must be joined before the first skin has been formed on the adhesive (skin-over time).

## Storage

When unopened and stored at room temperature (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

13050085	Silicone HT 300 85 ml red
13050310	Silicone HT 300 310 ml red

## Accessories:

13250000	Cartridge Cutter, 310 ml
13250001	Cartridge Gun, 310 ml
13250002	Cartridge Gun Special, 310 ml
13250009	Compressed Air Cartridge Gun, 310 ml
13955031	V-Joint Nozzle, 310 ml