

Speed-Flex® Crystal MS-Polymer



Gap filling up to max.	5 mm
Gap width up to max.	25 mm
Shelf life (+5°C to +25°C / +41°F to +77°F)	12 months
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	40
Elongation at break (DIN 53504/ASTM D 2240) ± 5	300 %
Tensile strength of pure adhesive and sealant	3,0 N/mm ²
Average tensile shear strength (DIN EN 1465/ ASTM D 12)	2,0 N/mm ²
Specific resistance	0,9 x 10 ¹² Ohm/cm
Tear strength (DIN 53515/ASTM D 1002)	19 N/mm ²
Movement capacity max.	20 %
Overpaintable (liquid paint)	only „wet in wet“, within 3 hrs. at the latest
Building material category (DIN 412)	B 2
Specific forward resistance	0,9 x 10 ¹² Ohm/cm
Layer thickness	2,5 mm
Temperature resistance	-40 to +90 briefly (approx. 2 h) to +120 °C

*Measured at 50% relative air humidity and +23°C

crystal-clear adhesion

WEICON Speed-Flex Crystal replaces traditional fixings like screws, pegs, rivets etc. Due to the very high initial adhesion, bonding is possible even on vertical surfaces both in-house and outside.

Particularly suitable for optically demanding bondings when the adhesive bead is not to be visible. Thus e.g. transparent plastics, acrylic glass or other materials can be bonded rapidly, neatly and attractively among each other.

WEICON Speed-Flex Crystal can be used for drywall and interior work, metal construction, tank and apparatus engineering, in ventilation and air conditioning systems, in exhibition stand construction and shopfitting and in many other cases.

WEICON Speed-Flex Crystal is very strong, pasty, stable, resistant to ageing, weathering and UV rays and is free of silicone, isocyanate and halogen. ISEGA certificate for use in food technology.



Technical Data

Composition	1 C.-Polyoxypropylener
density	1,06 g/cm ³
Viscosity adhesive	pasty
Stability/Run-off (ASTM D 222)	< 1 mm
Processing temperature	+5 to +40 °C
Cure type	By humidity
Curing condition	+5 to +40°C and 30% to 95% rel. humidity
Skin-overtime*	10 min.
Curing speed (first 24h)	2 -3 mm
Volume change (DIN 52451)	-3 %

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Surface pre-treatment

The surfaces must be clean and free of grease. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the primer selection table. A mechanical surface pre-treatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

Processing

Application methods:

Professional cartridge gun for 310 ml cartridges (WEICON Cartridge Gun "special"), compressed air gun we recommend a variation with piston rod (WEICON Cartridge Gun) , automatic dosing systems.

Joining the parts to be bonded:

To ensure optimal wetting, the parts must be joined before the first skin has been formed on the adhesive (skin-overtime).

Storage

When unopened and stored at room temperature (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it

Available sizes:

13608310 Speed-Flex® Crystal MS-Polymer 310 ml

Accessories:

13250000 Cartridge Cutter, 310 ml
 13250001 Cartridge Gun, 310 ml
 13250002 Cartridge Gun Special, 310 ml
 13250009 Compressed Air Cartridge Gun, 310 ml
 13955031 V-Joint Nozzle,

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG
 (Headquarters)
 Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Turkey
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr
 www.weicon.com.tr

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com
 www.weicon.com.ro

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON South East Asia Pte Ltd
 Singapore
 phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weicon.cz
 www.weicon.cz

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es
 www.weicon.es

WEICON Italia S.r.l.
 Italy
 phone (+39) 0102924871
 info@weicon.it
 www.weicon.it