

#### **Technical Datasheet**

Create Date: 16.11.2017 - Seite 1/

# Adhesive Spray extra strong



## special product for strong and reliable adhesions

Adhesive Spray extra strong is a special formula for strong and permanent bonds on rough and uneven surfaces. A special valve allows the adhesive quantities to be adjusted with infinite variability.

WEICON Adhesive Spray extra strong can be used for the bonding of felt, PVC foil, imitation leather, carpets, plastics, cardboard, foam and cellular rubber, insulating materials, soft foam, vinyl, leather, rubber, metal and wood. It is also suitable for large-area adhesive bonding.

## **Technical Data**

Base	synthetic rubber
Processing temperature	+10 to +30 °C
Evaporation time	5 - 10 min.
Open time max.	45 min.
Effectivness	4 m²
Temperature resistance	-20 to +80 °C
Storage stability	12 months

The product is subject to natural color variations.

# **Processing**

1. Shake can before use. Surfaces must be dry, clean and free of grease. Spray on one surface at about 15 to 30 cm distance. With porous materials, Adhesive Spray should be applied on both surfaces. 2. Depending on surface characteristics and ambient temperature, let the spray dry (approx. 10 minutes) until the adhesive is no longer stringy. 3. Position the parts and join them with strong pressure.

## Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding  $+50^{\circ}$ C.

# Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

## Available sizes:

11801500 Adhesive Spray extra strong 500 ml

## Accessories:

11202400 Sealant and Adhesive Remover, 400 ml

11207400 Surface Cleaner, 400 ml 11850200 Hand Protective Foam, 200 ml

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com