



Safety Data Sheet

Page 1 of 11

LOCTITE 407 LOW VISCOSITY known as 407 INSTANT
ADHESIVE IN JP 50

SDS No. : 173122

V001.8

Revision: 12.04.2016

printing date: 05.03.2020

Section 1. Identification of the substance/preparation and of the company/undertaking

Product name: LOCTITE 407 LOW VISCOSITY known as 407 INSTANT ADHESIVE IN JP 50

Other means of identification: LOCTITE 407 BO50G EN/CH/JP

Product code: IDH243277

Recommended use of the chemical and restrictions on use

Intended use: Adhesive

Identification of manufacturer, importer or distributor

Importer: Henkel Singapore Pte Ltd 401 Commonwealth Drive, #03-01/02, Haw Par Technocentre, Singapore. 149598
Phone : +65 62660100 Fax : +65 62661161

E-mail address of person responsible for Safety Data Sheet: ap-ua-psra.sea@henkel.com

Emergency information: FOR EMERGENCIES ONLY (Spill, major leak, Fire, Exposure, or Accident). Call CHEMTREC: +1 703-741-5970

Section 2. Hazards identification

GHS Classification:

<u>Hazard Class</u>	<u>Hazard Category</u>	<u>Target organ</u>
Skin corrosion/irritation	Category 2	
Serious eye damage/eye irritation	Category 2	
Specific target organ toxicity - single exposure	Category 3	respiratory tract irritation

GHS label elements:

Hazard pictogram:



Signal word:

Warning

Hazard statement: H315 Causes skin irritation.
H319 Causes serious eye irritation.
H335 May cause respiratory irritation.

Precaution:

Prevention: P261 Avoid breathing dust/fume/gas/mist/vapours/spray.
P264 Wash hands thoroughly after handling.
P272 Contaminated work clothing should not be allowed out of the workplace.
P280 Wear eye protection/face protection.
P280 Wear protective gloves.

Response: P302+P352 IF ON SKIN: Wash with plenty of water.
P304+P340+P312 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell.
P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P332+P313 If skin irritation occurs: Get medical advice/attention.
P337+P313 If eye irritation persists: Get medical advice/attention.
P362+P364 Take off contaminated clothing and wash it before reuse.

Storage: P403+P233 Store in a well-ventilated place. Keep container tightly closed.

Disposal: P501 Dispose of contents/container to an appropriate treatment and disposal facility in accordance with applicable laws and regulations, and product characteristics at time of disposal.

Section 3. Composition / information on ingredients

Substance or Mixture:
Mixture

Declaration of hazardous chemical:

Hazard component CAS-No.	Content	GHS Classification
Ethyl 2-cyanoacrylate 7085-85-0	60- 100 %	Skin irritation 2 H315 Serious eye damage/eye irritation 2 H319 Target Organ Systemic Toxicant - Single exposure 3 H335
Phthalic anhydride 85-44-9	0.1- 1 %	Acute toxicity 4; Oral H302 Skin irritation 2 H315 Serious eye damage/eye irritation 1 H318 Respiratory Sensitization 1 H334 Skin Sensitization 1 H317 Target Organ Systemic Toxicant - Single exposure 3 H335
Hydroquinone 123-31-9	< 0.1 %	Acute toxicity 4; Oral H302 Serious eye damage/eye irritation 1 H318 Skin Sensitization 1 H317 Germ cell mutagenicity 2 H341 Carcinogenicity 2 H351 Acute hazards to the aquatic environment 1 H400 Chronic hazards to the aquatic environment 1 H410

Section 4. First aid measures

- Inhalation:** Move to fresh air, consult doctor if complaint persists.
- Skin contact:** Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such as a spoon, preferably after soaking in warm soapy water.
Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate enough heat to cause a burn.
Burns should be treated normally after the adhesive has been removed from the skin.
If lips are accidentally stuck together apply warm water to the lips and encourage maximum wetting and pressure from saliva inside the mouth.
Peel or roll lips apart. Do not try to pull the lips apart with direct opposing action.
- Eye contact:** If the eye is bonded closed, release eyelashes with warm water by covering with wet pad.
Cyanoacrylate will bond to eye protein and will cause periods of weeping which will help to debond the adhesive.
Keep eye covered until debonding is complete, usually within 1-3 days.
Do not force eye open. Medical advice should be sought in case solid particles of cyanoacrylate trapped behind the eyelid cause any abrasive damage.

Ingestion: Ensure that breathing passages are not obstructed. The product will polymerise immediately in the mouth making it almost impossible to swallow. Saliva will slowly separate the solidified product from the mouth (several hours).

Indication of immediate medical attention and special treatment needed: See section: Description of first aid measures

Section 5. Fire fighting measures

Suitable extinguishing media: Foam, extinguishing powder, carbon dioxide.
Fine water spray

Improper extinguishing media: High pressure waterjet

Specific hazards arising from the chemical: In the event of a fire, carbon monoxide (CO), carbon dioxide (CO₂) and nitrogen oxides (NO_x) can be released.

Special protection equipment and precautions for firefighters: Fire fighters should wear positive pressure self-contained breathing apparatus (SCBA).

Section 6. Accidental release measures

Personal precautions: Ensure adequate ventilation.

Environmental precautions: Do not let product enter drains.

Clean-up methods: Do not use cloths for mopping up. Flood with water to complete polymerization and scrape off the floor. Cured material can be disposed of as non-hazardous waste.

Section 7. Handling and storage

Handling: Ventilation (low level) is recommended when using large volumes
Use of dispensing equipment is recommended to minimise the risk of skin or eye contact

Storage: For optimum shelf life store in original containers under refrigerated conditions at 2 - 8°C (35.6 - 46.4 °F)

Section 8. Exposure controls / personal protection

Components with specific control parameters for workplace:

ETHYL CYANOACRYLATE 7085-85-0	Value type	Time Weighted Average (TWA):
	ppm	0.2
	Remarks	ACGIH
PHTHALIC ANHYDRIDE 85-44-9	Value type	Time Weighted Average (TWA):
	ppm	1
	Remarks	ACGIH
PHTHALIC ANHYDRIDE 85-44-9	Value type	Time Weighted Average (TWA):
	ppm	1
	mg/m³	6.1
	Remarks	SG PEL
HYDROQUINONE 123-31-9	Value type	Time Weighted Average (TWA):
	mg/m³	1
	Remarks	ACGIH
HYDROQUINONE (DIHYDROXY BENZENE) 123-31-9	Value type	Time Weighted Average (TWA):
	mg/m³	2
	Remarks	SG PEL

Respiratory protection:

Ensure adequate ventilation.
An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area
Filter type: A (EN 14387)

Hand protection:

The use of chemical resistant gloves such as Nitrile is recommended.
Polyethylene or polypropylene gloves are recommended when using large volumes.
Do not use PVC, rubber or nylon gloves.
Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed then the gloves should be replaced.

Eye protection:

Wear protective glasses.
Protective eye equipment should conform to EN166.

Body protection:

Wear suitable protective clothing.
Protective clothing should conform to EN 14605 for liquid splashes or to EN 13982 for dusts.

Engineering controls:

Ensure good ventilation/extraction.

Hygienic measures:

Wash hands before work breaks and after finishing work. Do not eat, drink or smoke while working. Good industrial hygiene practices should be observed.

Section 9. Physical and chemical properties

Appearance:

colourless

Odor:

liquid
irritating

Odor threshold (CA):

No data available.

pH:	No data available.
Melting point / freezing point:	No data available.
Specific gravity:	No data available.
Boiling point:	> 149 °C (> 300.2 °F)
Flash point:	80 - 93 °C (176 - 199.4 °F)
Evaporation rate:	No data available.
Flammability (solid, gas):	No data available.
Lower explosive limit:	No data available.
Upper explosive limit:	No data available.
Vapor pressure: (; 25.0 °C (77 °F))	0.6600000 mbar
Vapor density:	No data available.
Density:	1.0700 g/cm3
Solubility:	No data available.
Partition coefficient: n-octanol/water:	No data available.
Auto ignition:	No data available.
Decomposition temperature:	No data available.
Viscosity:	No data available.
VOC content: (2010/75/EC)	< 3.00 %

Section 10. Stability and reactivity

Reactivity/Incompatible materials:	Rapid exothermic polymerization will occur in the presence of water, amines, alkalis and alcohols.
Chemical stability:	Stable under recommended storage conditions.
Conditions to avoid:	No decomposition if used according to specifications.
Hazardous decomposition products:	None if used for intended purpose.

Section 11. Toxicological information

Symptoms of Overexposure:	EYE: Irritation, conjunctivitis. SKIN: Redness, inflammation. RESPIRATORY: Irritation, coughing, shortness of breath, chest tightness.
---------------------------	--

Acute oral toxicity:

Ethyl 2-cyanoacrylate 7085-85-0	Value type	LD50
	Value	> 5,000 mg/kg
	Species	rat
	Method	OECD Guideline 401 (Acute Oral Toxicity)
Phthalic anhydride 85-44-9	Value type	LD50
	Value	1,530 mg/kg
	Species	rat
	Method	
Hydroquinone 123-31-9	Value type	LD50
	Value	367 mg/kg
	Species	rat
	Method	OECD Guideline 401 (Acute Oral Toxicity)

Acute dermal toxicity:

Ethyl 2-cyanoacrylate 7085-85-0	Value type	LD50
	Value	> 2,000 mg/kg
	Species	rabbit
	Method	OECD Guideline 402 (Acute Dermal Toxicity)
Phthalic anhydride 85-44-9	Value type	LD50
	Value	> 10,000 mg/kg
	Species	rabbit
	Method	

Skin corrosion/irritation:

Ethyl 2-cyanoacrylate 7085-85-0	Result	slightly irritating
	Exposure time	24 h
	Species	rabbit
	Method	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

Serious eye damage/irritation:

Ethyl 2-cyanoacrylate 7085-85-0	Result	irritating
	Exposure time	72 h
	Species	rabbit
	Method	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Phthalic anhydride 85-44-9	Result	highly irritating
	Exposure time	
	Species	rabbit
	Method	

Respiratory or skin sensitization:

Ethyl 2-cyanoacrylate 7085-85-0	Result	not sensitising
	Test type	
	Species	guinea pig
	Method	
Phthalic anhydride 85-44-9	Result	sensitising
	Test type	in vivo
	Species	guinea pig
	Method	
Phthalic anhydride 85-44-9	Result	sensitising
	Test type	Mouse local lymphnode assay (LLNA)
	Species	mouse
	Method	Mouse local lymphnode assay (LLNA)
Hydroquinone 123-31-9	Result	sensitising
	Test type	Guinea pig maximisation test
	Species	guinea pig
	Method	

Germ cell mutagenicity:

Ethyl 2-cyanoacrylate 7085-85-0	Result	negative
	Type of study / Route of administration	bacterial reverse mutation assay (e.g Ames test)
	Metabolic activation / Exposure time	
	Method	OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Ethyl 2-cyanoacrylate 7085-85-0	Result	negative
	Type of study / Route of administration	mammalian cell gene mutation assay
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Ethyl 2-cyanoacrylate 7085-85-0	Result	negative
	Type of study / Route of administration	in vitro mammalian chromosome aberration test
	Metabolic activation / Exposure time	with and without
	Method	OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test)
Phthalic anhydride 85-44-9	Result	negative
	Type of study / Route of administration	bacterial reverse mutation assay (e.g Ames test)
	Metabolic activation / Exposure time	with and without
	Method	
Hydroquinone 123-31-9	Result	negative
	Type of study / Route of administration	bacterial reverse mutation assay (e.g Ames test)
	Metabolic activation / Exposure time	with and without
	Method	EU Method B.13/14 (Mutagenicity)

Repeated dose toxicity:

Hydroquinone 123-31-9	Result	NOAEL=>= 250 mg/kg
	Route of application	oral: gavage
	Exposure time / Frequency of treatment	14 days5 days/week. 12 doses
	Species	rat
	Method	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)
Hydroquinone 123-31-9	Result	LOAEL=<= 500 mg/kg
	Route of application	oral: gavage
	Exposure time / Frequency of treatment	14 days5 days/week. 12 doses
	Species	rat
	Method	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)

Section 12. Ecological information

Ecotoxicity:

Do not empty into drains / surface water / ground water.

Toxicity:

Phthalic anhydride 85-44-9	Value type	LC50
	Value	313 mg/l
	Acute Toxicity Study	Fish
	Exposure time	48 h
	Species	Leuciscus idus
	Method	DIN 38412-15
Phthalic anhydride 85-44-9	Value type	EC50
	Value	68 mg/l
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Selenastrum sp.
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Phthalic anhydride 85-44-9	Value type	EC 50
	Value	> 1,000 mg/l
	Acute Toxicity Study	Bacteria
	Exposure time	3 h
	Species	
	Method	ISO 8192 (Test for Inhibition of Oxygen Consumption by Activated Sludge)
Hydroquinone 123-31-9	Value type	LC50
	Value	0.638 mg/l

	Acute Toxicity Study	Fish
	Exposure time	96 h
	Species	Oncorhynchus mykiss
	Method	OECD Guideline 203 (Fish, Acute Toxicity Test)
Hydroquinone 123-31-9	Value type	EC50
	Value	0.134 mg/l
	Acute Toxicity Study	Daphnia
	Exposure time	48 h
	Species	Daphnia magna
	Method	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Hydroquinone 123-31-9	Value type	EC50
	Value	0.335 mg/l
	Acute Toxicity Study	Algae
	Exposure time	72 h
	Species	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)
	Method	OECD Guideline 201 (Alga, Growth Inhibition Test)
Hydroquinone 123-31-9	Value type	EC 50
	Value	0.038 mg/l
	Acute Toxicity Study	Bacteria
	Exposure time	30 min
	Species	
	Method	

Persistence and degradability:

Ethyl 2-cyanoacrylate 7085-85-0	Result	
	Route of application	aerobic
	Degradability	57 %
	Method	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Phthalic anhydride 85-44-9	Result	
	Route of application	aerobic
	Degradability	90 %
	Method	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Hydroquinone 123-31-9	Result	readily biodegradable
	Route of application	aerobic
	Degradability	75 - 81 %
	Method	EU Method C.4-E (Determination of the "Ready" Biodegradability Closed Bottle Test)

Bioaccumulative potential / Mobility in soil:

Ethyl 2-cyanoacrylate 7085-85-0	LogKow	0.776
	Temperature	22 °C
	Method	EU Method A.8 (Partition Coefficient)
Phthalic anhydride 85-44-9	LogKow	1.6
	Temperature	
	Method	
Hydroquinone 123-31-9	LogKow	0.59
	Temperature	
	Method	EU Method A.8 (Partition Coefficient)

Section 13. Disposal considerations

Product

Method of disposal:

Cured adhesive: Dispose of as water insoluble non-toxic solid chemical in authorised landfill or incinerate under controlled conditions.
Dispose of in accordance with local and national regulations.
Contribution of this product to waste is very insignificant in comparison to article in which it is used

Packaging

Disposal of uncleaned packages: After use, tubes, cartons and bottles containing residual product should be disposed of as chemically contaminated waste in an authorised legal land fill site or incinerated. Disposal must be made according to official regulations.

Section 14. Transport information

Road transport ADR:

Not dangerous goods

Railroad transport RID:

Not dangerous goods

Inland water transport ADN:

Not dangerous goods

Marine transport IMDG:

Not dangerous goods

Air transport IATA:

Class:	9
Packing group:	III
Packaging instructions (passenger):	964
Packaging instructions (cargo):	964
UN no.:	3334
Label:	9
Proper shipping name:	Aviation regulated liquid, n.o.s. (Cyanoacrylate ester)
Additional Information:	Primary packs containing less than 500ml are unregulated by this mode of transport and may be shipped unrestricted.

Section 15. Regulatory information

Regulatory Information: Workplace Safety And Health Act (Chapter 354A) Workplace Safety And Health (Approved Codes of Practice) Notification 2013 SS586 Specification for Hazard Communication for hazardous chemicals and dangerous good Part 1,2,3

Global inventory status:

Regulatory list	Notification
TSCA	yes
AICS	yes
DSL	yes
ENCS (JP)	yes
KECI (KR)	yes
PICCS (PH)	yes
IECSC	yes
ISHL (JP)	yes
NZIOC	yes

Section 16. Other information

Disclaimer:

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.