PE-PP

Structural Acrylic Adhesives

Easy-Mix PE-PP 50 Structural Acrylic Adhesive



transparent | for low surface energy plastics | for small bonding gaps

WEICON Easy-Mix PE-PP 50 is a 2-component construction adhesive based on methyl acrylate. Due to its transparent curing, it is particularly suitable for visually appealing, highstrength adhesive bonding of low surface energy plastics, such as PE, PP and TPE. Thanks to its special formula, the adhesive is suitable for zero-gap bonds and for connecting surfaces with extremely small bonding gaps of less than 0,2 mm. The structural adhesive has a fast strength buildup and a high final strength. It is impact-resistant, ageingresistant, chemical-resistant, and slightly thixotropic. PE-PP 50 has a short pot life of six minutes and a processing time of twelve minutes. It is applied with a 1:1 system and does not require pre-treatment of the bonding surfaces, as the adhesive has an integrated primer. For the application of the Easy-Mix product, the Dispenser Easy-Mix D 50 is required.

Characteristics		
Base		methyl methacrylate
Texture		pasty
Colour		transparent
Processing		
Processing procedure		Easy-Mix
Mixing ratio by weight		1:1
Viscosity of the mixture		20.000 mPa⋅s
Density of the mixture		1 g/cm ³
Gap bridging up to max.		0 - 1,00 mm
Curing		
Pot life	at 20 °C	6 min.
Handling strength	(35 % strength)	12 min.
Final strength	(100 % strength)	24 h

Mechanical properties after curing

Lap shear strength material thickn. 1,5mm D	DIN EN 1465
Steel 1.0338 sandblasted	12 MPa
Stainless steel V2A sandblasted	11 MPa
Aluminium sandblasted	12 MPa
Galvanized steel	7 MPa
PVC-rigid roughened	12 MPa
CFRP	12 MPa
ABS	3 MPa
PC (polycarbonate)	6 MPa
GFRP	15 MPa
PMMA	8 MPa
Polyamide 6.6	2 MPa
PE-HD	12 MPa
PP (polypropylene)	8 MPa
Thermal parameters	
Temperature resistance	-50 °C to +80 °C, briefly up to +100 °C

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface pre-treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner). Smooth surfaces can be roughened mechanically.

Mixing

PE-PP 50 products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5C and below, no reaction takes place.

Processing

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5C and below, no reaction takes place.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user basers the only for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

Easy-Mix PE-PP 50 Structural Acrylic Adhesive

Storage

12 months at +2°C to +7°C; 3 months at +20°C to +25°C

Scope of delivery

Adhesive | Quadro Mixing Nozzle

Accessories

Dispenser Easy-Mix D 50, 1 PCE 10653050 10650005 Quadro Mixing Nozzle, 1 PCE

Conversion table

(°C x 1,8) + 32 = °F	Nm x 8,851 = lb∙in
mm/25,4 = inch	Nm x 0,738 = lb·ft
µm/25,4 = mil	Nm x 141,62 = oz∙in
N x 0,225 = lb	mPa⋅s = cP
N/mm² x 145 = psi	N/cm x 0,571 = lb/in
MPa x 145 = psi	kV/mm x 25,4 = V/mil

Available sizes

10665024	Easy-Mix PE-PP 50 Structural Acrylic Adhesive,
	24 ml, transparent
10665025	Easy-Mix PE-PP 50 Structural Acrylic Adhesive,
	1 Set, transparent
10665050	Easy-Mix PE-PP 50 Structural Acrylic Adhesive, 50 ml, transparent

To the product detail



Note The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr





EICON®