

## Product: iglidur<sup>®</sup> Q2

19.11.2013

### General Properties:

density:	1.46 g/cm <sup>3</sup>
colour:	beige- brown
saturation with moisture absorption at 23°C / 50% r. h.:	1.1 weight %
saturation with water:	4.6 weight %

### Mechanical Properties:

flexural modulus:	8400 MPa
flexural strength:	240 MPa
max. permissible surface pressure at 20 °C:	120 MPa
Shore D hardness:	80

### Thermal Properties:

highest long term service temperature <sup>1)</sup> :	130°C
highest short term service temperature <sup>1), 2)</sup> :	200°C
highest short term ambient temperature <sup>1), 2)</sup> :	220°C
lowest service temperature:	-40°C

### Electrical Properties:

specific volume resistivity:	>10 <sup>13</sup> Ωcm
surface resistivity:	>10 <sup>11</sup> Ω

<sup>1)</sup> relaxation possible

<sup>2)</sup> without additional load; no movement