

# WEICON WR Epoxy Resin



**liquid**  
**steel-filled**  
**wear resistant**

WEICON WR is suitable for areas where metal parts are subjected to strong wear due to friction, as repairs and recasting of shafts, for pouring out bearings and cutting and punching tools, for the production of casting and profile milling models as well as drawing moulds, for under pouring machines and foundations and as a wear-resistant under layer before the final coating with WEICON Ceramic BL.

WEICON WR can be used in machine construction, tool construction, model and mould making, and in many other industrial applications.



## Technical Data

Composition	Epoxy resin steel-filled
Specific Properties	liquid, wear resistant
Colour after curing	black
Mixing ratio by weight resin/hardener	100:15
Density of the mixture (200g preparation)	2,3 g/cm <sup>3</sup>
Viscosity of the mixture	20.000 mPa·s
Consumption at a coating thickness of 1,0 mm	2,30 kg/m <sup>2</sup>
Maximum layer thickness for each working step	10 mm
Pot life at +20°C (+68°F) 200g preparation	45 min.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Curing time mechanical loads	16 h
Final strength after	24 h
Mean strength at +25°C (+77°F) acc. to DIN 53281-83 ASTM D 1002:	
Pressure	110 Mpa
Bending	80 Mpa
E-Modul	5.000 - 5.500 Mpa
Shore D (ATSM D 1706)	90
Shrinkage	0,02 %
Thermoforming resistance	+65 °C
Temperature resistance	-35 to +120 °C
ISSA-Code	75.509.15/16
IMPA-Code	81 29 47/48

Information about surface pre-treatment and processing can be found in the manual.

### Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +25°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

### Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

10300005	WEICON WR Epoxy Resin 0.5 kg
10300020	WEICON WR Epoxy Resin 2.0 kg

### Accessories:

10604025	Mould Release Agent Liquid F 1000, 250 ml
10604515	Mould Release Agent Wax P 500, 150 g
10850005	Glass Fibre Cloth Tape, 50 mm
10953001	Processing Spatula, short
10953003	Processing Spatula, long
10953010	Stirrer Stainless Steel,
11202400	Sealant and Adhesive Remover, 400 ml
11207400	Surface Cleaner, 400 ml
11450400	Mould Release Agent, 400 ml
11850200	Hand Protective Foam, 200 ml

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es