


Heat Shrink Polyolefin Tubing Ultra Thin Wall

multicomp PRO



Specifications:

Shrink Ratio : 2:1
 Operating Temperature : -55°C to 135°C
 Shrink Temperature : 100°C
 Material : Polyolefin
 Standard Colour : Black
 Type : SPTW
 Suitable for use in high-density wiring and other restrictive space applications

Specification Values

Property	Test Method	Values
Tensile Strength	ISO 37	10 MPa minimum
Ultimate Elongation	ISO37	250% minimum
Heat Shock	ASTM D2671 (4hrs at 250°C)	No dripping, cracking or flowing
Heat Ageing	ISO 188 (168hrs at 175°C)	
Ultimate Elongation	ISO 37	150% minimum
Low Temperature Flexibility	ASTM D2671 (4hrs at -55°C)	No cracking
Flammability	ASTM D876	Pass
Electric Strength	IEC 243	20kV/mm minimum
Corrosion (Copper Mirror)	ASTM D2671	No corrosion

Specification Table

Part Number	Nominal Diameter (Ordering Size)	Min. Expansion Diameter	Max. Recovered Diameter	Nominal Recovered Wall
SPTW12	1.2 (3/64)	1.2 (0.046)	0.6 (0.023)	0.18 (0.007)
SPTW16	1.6 (1/16)	1.6 (0.063)	0.8 (0.031)	
SPTW24	2.4 (3/32)	2.4 (0.093)	1.2 (0.046)	
SPTW32	3.2 (1/8)	3.2 (0.125)	1.6 (0.062)	
SPTW48	4.8 (3/16)	4.8 (0.187)	2.4 (0.093)	0.25 (0.01)
SPTW64	6.4 (1/4)	6.4 (0.25)	3.2 (0.125)	

Dimensions : Millimetres (Inches)

Newark.com/multicomp-pro
 Farnell.com/multicomp-pro
 Element14.com/multicomp-pro

multicomp PRO

Heat Shrink Polyolefin Tubing Ultra Thin Wall

multicomp PRO

Part Number Table

Description	Reel Length	Part Number
Ultra Thin Wall Heat Shrinkable Polyolefin Tubing	1.2 Meters	SPTW12
		SPTW16
		SPTW24
		SPTW32
		SPTW48
		SPTW64

Important Notice : This data sheet and its contents (the "Information") belong to the members of the AVNET group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp Pro is the registered trademark of Premier Farnell Limited 2019.

Newark.com/multicomp-pro
Farnell.com/multicomp-pro
Element14.com/multicomp-pro

multicomp PRO