

Chrome Yellow 1622

Version 2026-10-22b · Revision 2026-10-22

C.I. Name	Pigment Yellow 34	C.I. No.	77600
CAS No.	1344-37-2	Chemical Group	Inorganic Lead Chromate

Product Description

Chrome Yellow 1622 is a lemon shade yellow with semi-encapsulation for improved heat resistance. It is recommended for mid processing temperature up to 240C.

Physical Data

Density (g/cm ³)	5.5
Form of supply	Yellow Powder
Oil absorption (g/100 g)	20~22
Moisture (%)	≤1.5
pH value	7
Light fastness (scale 1–8)	3~4
Heat stability	240°C / 464°F

Chemical Resistance

Acid	4
Alkali	4
Alcohol	5
Ester	4
Ketone	4
Soap	5
Migration	5

Applications

Coatings	Plastics	Inks
Automotive Coating –	PVC ●	Offset –
Industrial Coating ●	PE/PP/PO ●	Solvent based –
Decorative Coating –	ABS ○	Water based –
Coil Coating ●	PS ○	UV / EB –
Wood Coating –	PA –	Inkjet –
Powder Coating ●	Rubber ●	

● Recommended ○ Limited suitability – Not recommended

Product Specification

Test Property	Specification	Test Method
ΔE	≤1.0	AFTM-P 2.1
Colour strength	100±5%	AFTM-P 2.1

Packaging, Shipping & Storage

Chrome Yellow 1622 is supplied as yellow powder. The product is packed in 25 kg paper bag and shipped on pallets of 1000 kg. Store under normal temperatures, dry and protected from weather. Shelf life: 5 years from manufacturing date.

All the information above is based on data obtained at laboratory and is not to be used for certifying the suitability of the product. Users are advised to test the product in their own system before purchase.