

Pigment Yellow 14RO

C.I. Name	Pigment Yellow 14
C.I. No.	21095

CAS. No.	5468-75-7
Chemical Group	Disazo

Product Description

Yellow 14RO is a very opaque and very reddish shade yellow pigment. It is suitable for all plastic applications up to the processing temperature of 180°C as well as various printing inks. We designed this pigment to be a potential replacement for mid-shade lead chrome pigments.

Physical Data

Density (g/cm3)	1.45~1.55
Form of Supply	Yellow Powder
Oil Absorption (mg/100g)	35~50
Moisture (%)	≤1.5
PH Value	7.0
Light Fastness	6.0
Heat Stability	180°C / 356°F

Chemical Resistance

Acid	5
Alkali	5
Alcohol	5
Ester	4
Ketone	4
Soap	4
Migration	4

Applications

- Coatings

Automotive Coating	-
Industrial Coating	-
Decorative Coating	-
Coil Coating	○
Wood Coating	-
Powder Coating	○

- Plastics

PVC	●
PE/PP/PO	●
ABS	-
PS	-
PA	-
Rubber	●

- Inks

Offset Ink	○
Solvent based	○
Water based	○
UV / EB	○
Inkjet	○

● Recommend

○ Limited Suitability

- Not Recommended

Product Specification

Test Property	Specification	Test Method
dE	≤1.0	AFTM-P 2.1
Color Strength	100±5%	AFTM-P 2.1

Packaging, Shipping & Storage

Pigment Yellow 14RO is supplied in powder form. The product is packed in 25kg/55lb paper bag and shipped on pallets (400kg). Please keep the product stored under normal temperatures, dry and protected from weather.

All the information above is based on data obtained at laboratory and is not to be used for certifying the suitability of the product. Users are advised to test the product in their own system before purchase.