

Verify this report at bellerophonlab.com

Images are approximate



ROUGH SAPPHIRE

Testing by Bellerophon



CUT SAPPHIRE

Testing by Bellerophon

GEMMOLOGICAL REPORT | RAPPORT GEMMOLOGIQUE REPORT No. R-202142321
Bellerophon Gemlab S.A.S January 30, 2023
16 Place Vendôme, 75001 Paris France

Most of the data collected on your item is available online. It may include FTIR, EDXRF, PL532, PL313, UV-vis, LIBS and/or Raman

DETAILS & RESULTS

Description One transparent gemstone
Weight 0.491 ct
Measurements 4.21 x 4.15 x 3.19 mm
Shape Cushion
Identification Natural S A P P H I R E
Colour Pink

Comment: No indications of heating

Geographic Origin: Mozambique
Sapphire from Mozambique formed ~600 m.y.a

Fluorescence: Medium red

M.P.H. Curti, GG
Chief gemmologist

T. Rozet, ATC, GA
Gemmologist

Rough Sapphire Testing by Bellerophon | Gemlab

Date of testing : October 27, 2021
Weight: 3.426 ct
Measurements: 10.71 x 6.85 x 4.54 mm

According to documents of "Fura Gems", the rough sapphire described above, was mined in its deposit in Mozambique. It was auctioned in Bangkok in September 2022.

The consistency of the analytical data collected during the examination of the rough sapphire and the faceted stone, as well as the comparison of their inclusion scenarios provided sufficient evidence to conclude that this stone was cut from that rough piece.

Verify and download digital report at bellerophonlab.com. Included 360 video & 3D scan

