



SPECIFICATIONS FOR THE USE OF **GIBCO'S PRF**

Plaster and Stucco Mortar

The plaster or stucco used shall comply with ASTM C926 "Standard Specification for Application of Portland Cement-Based Plaster" and adhere to the mix recommendations in table 2 for type C or CL plaster mixes and Table 3 for Type F or FL plaster mixes. GIBCO'S PRF is used in lieu of lime in these mix designs stated above.

MIX DESIGN	PORTLAND CEMENT TYPE I or II	GIBCO'S PRF	SAND
Scratch Coat 1 st Coat	1 Bag	3oz	2.5-4 cft.
Brown Coat 2 nd Coat	1 Bag	3oz	3-5 cft.
Finish Coat 3 rd Coat	1 Bag	3oz	1.5-3 cft

The sand used must comply with ASTM C144 "Standard Specification for Aggregate for Masonry Mortar" or ASTM C897 Standard Specification for Aggregate for Job-Mixed Portland Cement-Based Plasters"